

# Material knowledge the basis of Powder Metallurgy and Additive Manufacturing





# Material knowledge the base of Powder Metallurgy and Additive Manufacturing

Jan Opschoor

Eindhoven 16/04/2014



### **Overview**

Introduction powder metallurgy (PM)

High performance Tungsten components by Metal Injection Moulding (MIM)

Additive Manufacturing (AM) of ceramics Introduction to Digital Light Processing (DLP)


Additive Manufacturing (AM) of metals

What does ECN offer You




### Powder Metallurgy (PM) basic process









- Particle size, distribution, shape
- Impurities
- Homogeneity
- Stability
- Strength green product
- Sintering dopes
- Sintering ambient, Temp
- Density / porosity
- Strength
- Hardness
- De-gassing




## Unique features MIM and AM (PM based)

- Free Shaping, avoiding machining
- Isotropic properties and microstructure
- Ultra high purity materials
- Flexibility by unique alloying/doping
- Less energy consumption, less loss of material, less process steps




### MIM W: the process





### Net shaped W components




Mockup manufactured by Ansaldo



As sintered mono-blocks and mock up for ITER divertor target



As sintered bolts



Fine structures possible




Internal voids e.g. cooling channels possible



Tensile test component




### Microstructure control






## TEM of W doped with 1 vol.%Y<sub>2</sub>O<sub>3</sub>




# 1,2,3 => ODS particles # 4,5,6 => pre-existing pores

- ODS particles are almost uniformly spread inside the material volume, mainly as inclusions in the W grains
- W grains containing more than one oxide inclusion are observed everywhere





## HRTEM of pure W






### Pure tungsten

Density bars
Density squares
Thermal conductivity (25°C)
Hardness
Grain size

98,8 %
 99,0 %
 177,2 Wm<sup>-1</sup>K<sup>-1</sup>
 376 HV<sub>30</sub>
 17,2 μm












# 2-component MIM mock-up production






# 2-component MIM mock-ups production







### Additive Manufacturing (AM) of ceramics



- Project started January 2013
- November 2013: ADMATEC founded
  - Delivers printed components
  - Formatec at booth 118

### Role ECN

- Slurry / Process development
- Characterization



Thursday 15:35-16:00 Genderfoyer


Waar keramiek printen een plek vindt in de markt van keramische producten

Michiel de Bruijcker, Formatec Ceramics BV

Jan Opschoor 13



# DLP type printing (slurry based technology)







15


### Results AM ceramics

Materials: Alumina and Zirconia



 Developed 98% dense alumina having wall thicknesses up to 1 cm.







# Additive Manufacturing (AM) of metals #ECN and other light absorbing materials



- Slurry based technology
- Digital Light Processing (DLP) type printing
- Started with 316L
  - Severe light absorption
- Optimal alignment between
  - Used metal powder (e.g. grain size)
  - Resin
  - Additives
  - Curing radiation

Improved density microstructure roughness No de-gassing




### Microstructure of printed 316L steel

### • First results:

Printed body of several hundreds of layer







### What does ECN offer You?

- A route to your 3D shaped and precise products in ceramics and metals
- Small scale production of your 3D shaped and precise products in metals
- Optimization of your production/manufacturing process
- Characterization of your material to improve your quality
- Adaptation of your design due to the new product quality
- A warm welcome and more information at ECN booth no 58



### **Materials**

Solutions by knowledge and analysis

- Material characterisation
- Failure analysis
- Product optimisation
- Production development
- Joining technology
- Powder metallurgical material processing



# **Engineering & Realisation**Solutions beyond the state of art

- Process
- Mechanical
- Electrical
- Software
- Commissioning
- HAZOP studies



### **Metal Injection Moulding**

*Products of extreme materials* 

- Netshape manufacturing
- Refractory metals up to 3000°C
- No residual stresses
- No recrystallisation





### Thanks for your attention

### Opschoor@ecn.nl eee@ecn.nl

#### **ECN**

High Tech Campus 21 P.O. Box 1

5656AE Eindhoven 1755 ZG Petten The Netherlands The Netherlands

T+31 88 515 49 49 eee@ecn.nl F+31 88 515 44 80 www.ecn.nl

