Contents lists available at ScienceDirect



Renewable and Sustainable Energy Reviews

journal homepage: www.elsevier.com/locate/rser



Review of degradation and failure phenomena in photovoltaic modules

M. Aghaei^{a,b}, A. Fairbrother^c, A. Gok^d, S. Ahmad^{e,f}, S. Kazim^{e,f}, K. Lobato^g, G. Oreski^h, A. Reinders^{a,i}, J. Schmitz^j, M. Theelen^k, P. Yilmaz^{j,k}, J. Kettle^{1,*}

^a Energy Technology Group, Department of Mechanical Engineering, Eindhoven University of Technology, 5612 AE, Eindhoven, the Netherlands

^b Department of Ocean Operations and Civil Engineering, Norwegian University of Science and Technology (NTNU), 6009, Alesund, Norway

^c École Polytechnique Fédérale de Lausanne (EPFL), Institute of Electrical and Micro Engineering (IEM), Photovoltaics and Thin Film Electronics Laboratory, Rue de la Maladière 71b. 2002. Neuchâtel. Switzerland

^d Department of Materials Science and Engineering, Gebze Technical University, Gebze, Kocaeli, 41400, Turkey

e BCMaterials, Basque Center for Materials, Applications and Nanostructures, UPV/EHU Science Park, 48940, Leioa, Spain

f IKERBASQUE, Basque Foundation for Science, 48009, Bilbao, Spain

^g Instituto Dom Luiz, Faculdade de Ciências, Universidade de Lisboa, 1749-016, Lisboa, Portugal

^h Polymer Competence Center Leoben GmbH, Roseggerstrasse 12, 8700, Leoben, Austria

¹ Department of Design, Production and Management, Faculty of Engineering Technology, University of Twente, 7500, AE, Enschede, the Netherlands

^j MESA+ Institute for Nanotechnology, University of Twente, 7500, AE, Enschede, the Netherlands

^k TNO Partner in Solliance, High Tech Campus 21, 5656, AE, Eindhoven, the Netherlands

¹ James Watt School of Engineering, University of Glasgow, Glasgow, Scotland, UK

ARTICLE INFO

Keywords: solar Modules Solar cells Photovoltaics Reliability Degradation Wear-out Stress Climate Energy payback time

ABSTRACT

The degradation of photovoltaic (PV) systems is one of the key factors to address in order to reduce the cost of the electricity produced by increasing the operational lifetime of PV systems. To reduce the degradation, it is imperative to know the degradation and failure phenomena. This review article has been prepared to present an overview of the state-of-the-art knowledge on the reliability of PV modules. Whilst the most common technology today is mono- and multi-crystalline silicon, this article aims to give a generic summary which is relevant for a wider range of photovoltaic technologies including cadmium telluride, copper indium gallium selenide and emerging low-cost high-efficiency technologies. The review consists of three parts: firstly, a brief contextual summary about reliability metrics and how reliability is measured. Secondly, a summary of the main stress factors and how they influence module degradation. Finally, a detailed review of degradation and failure modes, which has been partitioned by the individual component within a PV module. This section connects the degradation phenomena and failure modes to the module component, and its effects on the PV system. Building on this knowledge, strategies to improve the operational lifetime of PV systems and thus, to reduce the electricity cost can be devised. Through extensive testing and failure analysis, researchers now have a much better overview of stressors and their impact on long term stability.

1. Introduction

The economic and societal impact of photovoltaics (PV) is enormous and will continue to grow rapidly. To achieve the 1.5 °C by 2050 scenario, the International Renewable Energy Agency predicts that PV has to increase 15-fold and account for half of all electricity generation (15 TW), increasing from just under 1 TW in 2021 [1]. The quality and commercial attractiveness of a PV system is primarily determined by its performance in the field, cost, and lifetime, to each of which the PV module significantly contributes. During the operational lifetime of a module, it will be exposed to simultaneous environmental stresses like sunlight, heat and cold, moisture, and mechanical loads. These factors often lead to a gradual decrease of the performance, and in some cases to sudden breakdown and power loss. It is desirable to limit these effects. A recent European Technology and Innovation Platform report [2] highlighted the importance of long-term reliability. Engineers should minimize the degradation as much as possible, and quantitatively predict degradation phenomena that cannot be eliminated. This will enable a more accurate estimation of the expected service lifetime of a module and its electricity yield. Such estimates are required for large-scale investments, since investors, banks, and insurance companies desire to

* Corresponding author. E-mail address: jeff.kettle@glasgow.ac.uk (J. Kettle).

https://doi.org/10.1016/j.rser.2022.112160

Received 8 July 2021; Received in revised form 5 January 2022; Accepted 15 January 2022 Available online 3 February 2022

1364-0321/© 2022 The Authors. Published by Elsevier Ltd. This is an open access article under the CC BY license (http://creativecommons.org/licenses/by/4.0/).

Nomenclature				
ALT	Accelerated Life Testing			
c-Si	Crystalline Silicon			
CdTe	Cadmium Telluride			
CIGS	Copper Indium Gallium Selenide			
DSC	Dye-sensitized Solar Cells			
EPBT	Energy Pay Back Time			
EVA	Ethylene-Vinyl Acetate			
IEC	International Electrotechnical Commission			
LCOE	Levelized Cost Of Electricity			
LETID	Light and Elevated Temperature Induced Degradation			
LID	Light-Induced Degradation			
NREL	US National Renewable Energy Laboratory			
OPV	Organic Photovoltaic(s)			
PET	Poly-Ethylene Terephthalate			
PID	Potential-Induced Degradation			
PV	Photovoltaic(s)			
SEMI	Semiconductor Equipment and Materials Institute			
TCO	Transparent Conducting Oxide			
UV	Ultraviolet			

minimize their risks and uncertainties. To optimise reliability and predictability, and to enhance the module lifetime, it is crucial that degradation and failure mechanisms are known and can be easily recognized and contained.

This article aims to give an overview of state-of-the-art knowledge on reliability of PV systems and treats degradation mechanisms that generally affect PV technologies. We intend this article to be a concise and up-to-date introduction to this topic for the general reader and specifically for newcomers into the PV reliability engineering domain. For this review paper, existing literature published during the past 30 years has been explored by a team of experts from various organizations who are members of the working group on "Reliability and Durability of PV" in EU COST Action PEARL PV [3]. In the remainder of this section we will introduce the different photovoltaic technologies that are the dominant focus of industry and academia. Next, Section 2 will define the most important concepts and notions for reliability and degradation, describe the testing standards, and introduce the economic aspects of PV reliability. Section 3 describes the stress factors causing degradation in PV modules; Section 4 subsequently reviews the known degradation effects that arise from these stresses. Finally, the perspective of future research challgenges are highlighted in Section 5. A renewable energy technology such as PV will play a key role in the energy transistion to a

net-zero emission energy system, however, it is vital for the different PV technologies to continue evolving to allow for further cost reductions, but also to lower environmetnal impacts and for ease of re-use and recycling. It is clear that new device architectures and materials have to take into consideration scaling effects, ability to exhibit long lifetimes and low environmental impacts. This review paper summaries the reliability challenges which must be adhered to in order to achieve longer lifetime and ensure these further cost reductions are achieved.

2. Framework for reliability research and metrics n PV modules

2.1. Contemporary photovoltaic technologies

The most common configurations for c-Si and thin-film based PV modules are shown in Fig. 1. Solar cells are one of many components that make up the laminate structure. Other components include the module packaging (glass front cover, encapsulant, backsheet), internal circuit (electrodes, interconnects), bypass diodes, junction boxes, frame, cables, and connectors; all of which may influence or even limit the module's reliability.

Table 1

Comparison of PV technologies in terms of performance, maturity and market share. The market shares were estimated from data supplied by the Fraunhofer ISE [4]. Power conversion efficiencies were obtained from the Green et al. tables [5] and from the National Renewable Energy Laboratories (NREL) Website [6]. Energy payback time values are those reported by and Ludin et al. [7] unless specified otherwise. The review of Ludin et al. covers many studies published since the year 2000; the lower EPBT values in the Table relate to more recent products.

Technology	Year surpassing 10% eff.	2020 Market share (%)	Record cell efficiency (%)	EPBT (y)	Best literature report of outdoor lifetime (y)
Monocrystalline Si	1957 [8]	66.6	26.7	1.4–7.3	>20
Polycrystalline Si	1984	28.4	24.4	0.8–4.2	>20
CdTe	1981	4.1	22.1	0.8 - 2.7	>20
CIGS	1981	0.8	23.4	1.3 - 2.8	>20
Amorphous Si:H	1992	0.1	14.0	1.1 - 3.2	>20
Dye-sensitized Solar Cells	1997	-	12.3	0.6–1.8	<2 [9]
Organic Photovoltaics	2012	-	17.5	0.1–1 [<mark>41</mark>]	~2 [12, 13]
Perovskite Solar Cells	2012	-	25.5	0.2–5.4	<0.5 [14]



Fig. 1. The most common configurations of PV modules for crystalline silicon (left) and CdTe thin film (right) [15]. Rigid CIGS modules have a similar structure as CdTe modules but with the solar cells under the encapsulant. Besides these two basic configurations, a wide variety of alternative structures exists, e.g. using a polymer frontsheet or containing only flexible components [16].

Table 1 provides a summary of the major PV technologies considered. The table quantifies a trend that one would expect: earlier developed technologies had more time to mature and as a result, they show good efficiency and a good outdoor lifetime. With these properties, in combination with the economy of scale, contemporary photovoltaic systems can generate electricity at a very competitive cost level. The Energy Payback Time (EPBT), further treated in the next section, is of the order of one year for all technologies. Any PV system with a lifetime exceeding the EPBT can be viewed as renewable. The listed PV technologies easily meet this requirement except for the newest emerging ones, where lifetime problems still need to be resolved.

Although it is included in the table for completeness, hydrogenated amorphous silicon has not been reviewed in the remainder of this article as the rather low record efficiency has not improved much since the turn of the Century, indicating a limited potential to contribute to the energy transition. Dye-sensitized solar cells have persistent reliability issues but did lead to the development of the new class of perovskite solar cells. In view of their novelty and promising efficiencies, organic photovoltaics and perovskite solar cells may become serious contenders in the PV market when an affordable solution is found for their stability issues. We may conclude that besides power efficiency, the reliability is decisive for both the economic value and the environmental impact of PV technologies.

2.2. Reliability definitions and quality standards for photovoltaics

In the engineering domain, reliability is quantitatively defined as: *the probability that an item will perform a required function without failure under stated conditions for a stated period of time* [17]. In the context of PV, reliability emerges during the operational lifetime in the field, and thus affects financiers and owners. Quality control on the other hand takes place during fabrication of the modules as a responsibility of the manufacturer. However, reliability and quality are strongly interrelated. Low-quality manufacturing of PV modules will result in a low reliability of PV modules in the field. Conversely, we can assume that high quality materials, module design, and production will yield reliable PV systems. The quality control in present PV manufacturing lines results in an expected life span of PV modules, usually guaranteed to be 25 years, though there are noteworthy systems that have been in operation for over 30 years [18–20].

From a quality engineering point of view, PV modules are assessed against a specification, and ordinarily, a producer will sell a module after it passed design, type approval, and safety qualification standards [21]. PV standards were initiated in 1978 which was supported by the United States Department of Energy and managed by the Jet Propulsion Laboratory. As documented by Verlinden et al. [22], the task of developing standards was taken over by the Institute of Electrical and Electronic Engineers in the 1980s, then by the International Electrotechnical Commission (IEC), the Underwriters Laboratories and, as of 2015, by the Semiconductor Equipment and Materials Institute (SEMI). The original qualification standard for PV modules was called the "Block V Specification" and included a series of qualification tests. There are now a wide range (~170) of PV standards and technical specifications. However, the most well-known and widely used regarding durability are IEC 61215 and IEC 61730. Several countries have their own national PV-related standards, but they are for the most part based on the standards developed by the IEC. The Underwriters Laboratories standards are in general related to the safety of PV components or systems, while the SEMI standards are related to the manufacturing aspects.

However, meeting these standards and specifications provides no measure of the quality, performance, and failure over time, particularly beyond the warranty period. This marks the distinction between quality control and reliability engineering. In reliability engineering, we presume that failures will occur at statistically fluctuating time intervals, often depending on the weather and other stress conditions. So, whilst the PV community has developed standardized tests that assess the timezero quality of a PV module, it remains difficult to predict the long-term performance of PV modules installed in PV systems. Such predictions rely on reliability models that may be generic in engineering or specific for a given technology.

An important generic model is the bathtub curve, which describes most product life cycles; see Fig. 2. The bathtub accounts for both *degradation mechanisms* (which result in gradual reduction of performance over time) and *failure* (meaning the inability of components or modules to fulfil their designed function). In the bathtub curve, one distinguishes three stages:

- *Early life* failures are often related to poor design or manufacturing errors that can be reduced by effective process controls or screening. Typically, for PV modules these occur within 1–2 years of use;
- Failures during the *steady-state life* period are often either random or the result of technology limitations;
- *Wear-out* failures, caused by mechanisms that degrade the performance gradually until the device does not function anymore, are related to mechanical, physical or chemical phenomena such as fatigue, electromigration and corrosion. Ideally, wear-out failure only occurs after the warranty period expires.

Work has been conducted to relate failure modes of PV modules to regions in the bathtub curve. Koentges et al. [25] categorized failure modes of crystalline-silicon modules on the basis of data provided by an unnamed commercial distributor. They found that the most common causes of early failure are junction box failure, glass breakage, defective cell interconnect, loose frame, and delamination. A study by DeGraaff [26] on PV modules that had been in the field for at least 8 years estimated that around 2% of PV modules failed after 11-12 years. In this period, there was a much stronger prevalence of defective interconnections in the module, and failures due to PV module glass breakage, burn marks on cells (10%), and encapsulant failure (9%) while failures due to junction-boxes and cables remained high. Whilst these studies are very insightful, it is worth noting that the investigated modules were manufactured some 15-20 years ago. Advances in technology probably reduce known ageing issues, but meanwhile, new degradation phenomena might surface.

2.3. Economic considerations of reliability

A capital investor's decision to invest in photovoltaics is usually based on a financial prognosis and a ranking against other opportunities. Risks include, but are not limited to, module degradation and failure. Clearly, the financial performance indicators cannot be derived from a



Fig. 2. Bathtub curve [23] showing the typical probability of failures (the failure rate) over the technical lifetime of a product such as a photovoltaic module, where β refers to the 'shape parameter' of a probability distribution function (discussed further in Ref. [24]).

Renewable and Sustainable Energy Reviews 159 (2022) 112160

solar module's technical performance alone. There are several metrics used for modelling return on investments over time. Quantification of the capital outlay and operating & maintenance expenditure of the PV system and its estimated energy yield are necessary inputs for the stakeholders in an investment.

The levelized cost of electricity is perhaps the most referenced metric of PV system economics. In simple terms, the LCOE gives a levelized (average) cost of electricity generation over the life of the asset. The LCOE could be used to compare the cost of energy generated by a PV power plant with that of a fossil fuel generating unit or another renewable technology [27]. The calculation for the LCOE is the net present value of total life cycle costs of the PV project divided by the quantity of energy produced over the system life.

$$LCOE = \frac{Total \ Lifecycle \ Cost}{Total \ Lifetime \ Energy \ Production}$$
(1)

The above LCOE equation can be disaggregated for solar generation as follows:

annual costs). Fig. 3 shows the world averaged LCOE of PV as it developed over time [29], and predictions of its future development [30]. It dropped by an order of magnitude between 2008 and 2020. In most countries, the cost of electricity produced by PV is below that of the grid's spot price, meaning it is economically competitive with conventional electricity sources [31].

A further decrease of the LCOE is expected as manufacturing volumes grow while both performance and reliability increase. Because of factors such as irradiance, subsidy programs and land price, the levelized cost of electricity depends heavily on the location of the plant. The discount rate, tax rate and degradation rate also strongly influence the LCOE. The steep decline of the overall capital system cost caused by the lowering cell cost is slowing down (on this semilogarithmic scale) as different contributors to the overall expenses now become more prominent. Consequently, this will mean degradation and reliability will have a greater influence over LCOE in the coming years [32]. For example: as estimated in 2017, the LCOE will rise by 6-7% [33], if annual degradation increases by 0.5% abs. assuming a 1 €/Wp investment cost for a

$$LCOE = \frac{(\text{Initial Investment}) - \left[\sum_{n=1}^{N} \left(\frac{\text{Depreciation}^{n}}{(1+D_{r})^{n}}\right) x (\text{Tax rate})\right] + \left[\sum_{n=1}^{N} \left(\frac{\text{Annual costs}^{n}}{(1+D_{r})^{n}}\right) x (1 - \text{Tax rate})\right] - \left(\frac{\text{Residual value}}{(1+D_{r})^{n}}\right)}{\sum_{n=1}^{N} \left(\frac{\text{Initial}\frac{kWn}{kWp} x (1 - \text{System degradation rate})^{n}}{(1+D_{r})^{n}}\right)}$$
(2)

[28]where *N* is the system lifetime (in years) and D_r is the discount rate; which is the interest rate used to determine the present value of future cash flows. Clearly LCOE is heavily dependent on the degradation rate and the lifetime as these have a direct impact upon both the produced electric energy and the sum of the running costs (depreciation and



Fig. 3. The historic calculations (grey markers) and future estimates (line) of the levelized cost of electricity (LCOE) for utility scale silicon photovoltaic systems based upon the International Technology Roadmap for Photovoltaic (ITRPV) roadmap from 2020. The historic data estimates are from Ref. [29], prognosis from Ref. [30] assuming an annual irradiation of 1500 kWh(AC)/kW (DC). Note the logarithmic scale of the primary y-axis. Shown on the secondary y-axis is how the calculated Energy payback Time (EPBT) has changed since 2007 based upon work from Ref. [11], with recent reports from Refs. [37–39] using data [30] assuming an annual irradiation of 1600–1800 kWh(AC)/kW (DC). Both metrics have reduced as a result of the falling cost, increase in efficiency and increase in useful life of PV modules.

system sited in a high insolation area.

A second important metric for renewable energy systems is their Energy Pay Back Time (EPBT) (see Eq. (3) and Fig. 3), which is defined as the period required for a system to generate the same amount of energy (*in terms of equivalent primary energy*) that was used to produce (and manage at end-of-life) the system itself.

$$EPBT [years] = CED / \left(\left[E_{Agen} / \eta_G \right] - E_{O\&M} \right)$$
(3)

where CED is the cumulative energy demand [MJ], which includes material and system production energy, transportation and installation energy, and end-of-life management energy. E_{Agen} [MJ_{el}/yr] is the annual electricity generation, $E_{O&M}$ [MJ_{PE-eq}] is the annual primary energy demand for operation and maintenance, η_G is the grid efficiency, i.e. the average life-cycle primary energy to electricity conversion efficiency at the demand side [34]. Contrary to LCOE, EPBT is only moderately sensitive to degradation in mature PV technologies. Depending on the technology and location of the PV system, the EPBT today ranges from 0.4 to 1.5 years and has decreased by around 80% in the past decade due to wafer thinning and more efficient manufacturing (see Fig. 2) [35,36].

2.4. Outdoor reliability testing

The previous sections made clear that the power degradation and the lifetime of a PV technology need to be quantified. In laboratory settings, it is commonplace to undertake stress tests to examine for degradation modes in a systematic approach. However, as modules have improved in reliability, standard accelerated testing has become ineffective. Therefore, a degradation assessment needs to be complemented by outdoor data analysis. Often a combination of indoor accelerated and outdoor tests is used to conduct a failure modes and effects analysis, to assess the relative impact of different failures, in order to proactively improve PV design. In the United States the National Renewable Energy Laboratory (NREL) documented power degradation rates for different PV technologies and discussed the accuracies of different assessment approaches

[40,41]. In particular, NREL evaluated over 2000 modules tested in the field around the world and showed that degradation rates varied from 0.5% to 2% per year depending on the type and vintage. Their report concludes that for modules manufactured after the year 2000, the most stable material systems are polycrystalline Si and CdTe.

Outdoor performance is most commonly monitored by electrical curve tracing or maximum power point tracking, to produce a data set of delivered power (or efficiency) over time. Conventionally such data are then synthesized using a regression model, but data filtering and the selected model can dramatically influence results [42]. Advanced time series modelling can be used to reduce noise and inaccuracy [43–45]. An alternative is the year-on-year approach in which a degradation distribution is determined rather than a single (average) annual degradation rate [46]. Another report [47] has shown that degradation rates can be estimated from yield measurements, although the report adds the caveat that at least 3–4 years of data from at least 10 different PV systems are needed to obtain better than 1%/year accuracy.

The uncertainty on the estimation of the module power affects degradation rate calculations substantially. Temperature and irradiance are normally corrected, but experimental error, drift of sensors and plane of array irradiance still result in some uncertainty. Module shading and module coverage by soiling or snow can be notable yield-reducing factors as well. Also, the location on the system where the measurement has been taken can affect the analysis, for example, if output power is measured from the AC output, the degradation rate includes the inverter degradation as well [48,49]. Another important parameter in yield assessment is PV system availability and clearly the higher the data availability, the more accurate one can be with degradation rate calculation.

2.5. Accelerated testing and relationship to standards

Accelerated life testing (ALT) is an important part of the quality engineering process and uses stress levels higher than normal use conditions to speed up the formation and manifestation of defects. This allows reliability engineers to quickly identify failure modes, assess their relative severity and apply corrective actions. Historically, ALT protocols for reliability assessment of PV modules were developed to address known failures discovered in the field. As discussed in Section 2.1, most manufacturers utilize the international standard IEC 61215. However, failure mechanisms that are undiscovered in ALT are still being found in modules deployed in the field, often resulting in significant financial and energy production losses. Recent examples include backsheet cracking [50], potential-induced degradation (PID) [51], grid finger corrosion [52], light and elevated temperature induced degradation (LETID) [53] and snail trails [7], which are explained and discussed in more detail in Section 4.

Many of these result from a combination of stress factors which were not combined in conventional tests or may require much longer duration testing to be uncovered. Some, such as snail trails, follow from material interactions which were not discovered in component-level tests. As a result, there has been an increasing interest in extended, sequential, or combined stress factor testing [54,55]. Extended stress testing is described in IEC TS 63209. It takes approximately three times the duration of the module qualification tests laid out in IEC 61215. IEC TR 63279 describes the latest work on sequential and combined stress testing.

Alternatively, DuPont developed the module accelerated sequential testing [56], NREL the combined accelerated sequential testing [37] and Solliance the in-situ degradation method [58]. All three combine multiple stress factors such as light, humidity, temperature, rain, mechanical load and voltage stress. It is worth reminding that stress factors and stress levels in the outdoors are uncontrolled and time-varying, while conventional ALT approaches have a more monotonous character.

Finally, there has been significant effort to develop material and component tests for PV modules, such as the IEC 62788 series of standards. Whilst ALT is key to ongoing reliability programs where it can be used to identify material/supply issues in an early stage, quality engineering is becoming much more important as PV lifetimes extend beyond 30 years. As explained by Kurtz [59], quality assurance is key for identifying manufacturing defects from PV modules that later propagate into failures under operational conditions in the field.

3. Causes of module degradation

During real-world operation, PV modules are exposed to various external and internal stress factors that influence their performance and long-term reliability (see Fig. 4). While external stress factors are related to environmental conditions, internal stress factors are caused by the bill of materials of PV modules and processing related effects. External and internal stress factors are further described in Sections 3.1 and 3.2, respectively.

3.1. Environmental stress factors

3.1.1. Irradiance

The key characteristics of the incident solar irradiance on PV modules are its power, the spectral distribution and the angle of incidence. The global standard (AM 1.5G) solar spectral irradiance [60] covers the wavelength range of 280–4000 nm and corresponds to an integrated solar power of 1000 W/m². Although the UV region (280–400 nm) corresponds to only ~4.6% of this power, its photons are the most detrimental for polymeric materials upon prolonged exposure as the energy of these photons is high enough to cause scission of C–C and C–O bonds, which are typically found in the polymer main chain. These scission reactions lead to embrittlement and discoloration of the polymer [61].

The spectral distribution and intensity level of the incident irradiation depends on a number of factors such as variations in stratospheric ozone with latitude and season, time of the day, season, azimuth (compass angle), tilt angle from the horizontal, cloud cover, surface reflection, altitude, and air pollution [62]. UVB (280–315 nm) is the



Fig. 4. Some common PV module stressors for a silicon wafer-based PV module, including light ($h\nu$), strain (ε), voltage bias (V), chemical diffusion, ingress and egress (CH3COOH, H2O, O2, Na+), electric field (E), and thermomechanical strain (Δ T). Dimensions are not to scale.

most damaging part of the UV light, in particular for polymeric materials in PV modules although its power fraction (\sim 1.5%) is small compared to that of UVA (315–400 nm; \sim 98.5%) according to the reference spectrum. This fraction however fluctuates for the incident UV light [63]: it is higher at lower latitudes, during summer, and mid-afternoons, when the sun's rays are strongest, and faster degradation can be expected under such external conditions.

3.1.2. Temperature

Temperature is a key environmental stress factor as it may affect the electric performance of a PV module directly, accelerate permeation and reaction rates in materials, and induce mechanical stress due to differences in thermal expansion coefficients of module parts. The temperature within the cell or module may differ from the ambient temperature, particularly because of incident irradiance. The flow of heat out of the cells depends on the geometry and thermal conductivity of the surrounding materials, wind speed and the installation configuration of the PV module.

Temperature has an accelerating effect on many module degradation mechanisms particularly those related to chemical reactions and diffusion. The temperature dependence of such effects is often modelled using the Arrhenius equation with a mechanism-dependent activation energy [24,64]. The degradation of the encapsulant and backsheet films, and corrosion of the metallization elements follow Arrhenius behaviour.

Due to thermal expansion coefficient mismatches, module materials expand and contract at varying rates as temperature changes. This mismatch can induce thermo-mechanical stresses within the module construction. The mechanical stability of the active electrical elements, such as cells, solder joints, and interconnect ribbons, is particularly affected by such stresses. Deformation, delamination at the module interfaces and even cell cracking can result [65]. Variations in diurnal and seasonal temperatures produce cyclic thermo-mechanical stresses and this can lead to fatigue induced failures in the various module components.

3.1.3. Moisture

Moisture is also an important stress factor for PV modules as moisture ingress can deteriorate adhesive bonds at the interfaces between module components, resulting in delamination, causing loss of passivation and degrading anti-reflection coatings; and it leads to corrosion of metallization elements. In outdoor conditions, moisture appears in many forms such as water vapor (or humidity), condensation (or dew), rain, snow, and ice.

Since water vapor is in the gas form, it can permeate through polymeric packaging materials, accumulate within the module construction, and induce degradation of module components. Liquid water, mostly condensed humidity, dew, or rain, can be absorbed or desorbed as well [13]. Water ingress in larger quantities can induce mechanical stresses because of the hydro-dynamic volume expansion and contraction. It can also erode low molecular weight species and additives away from the polymeric materials. It can further dissolve ions, deteriorate the electrical insulation of dielectrics, and cause leakage current [66]. In the solid form as ice, it can experience volume change during freeze-thaw cycles and produce mechanical stresses on the outer side of the PV module that lead to delamination of the front glass or frame damage.

When the module is saturated with moisture, a drop in temperature can cause the moisture level to exceed its saturation limit leading to condensation in the form of water droplets especially at the interfaces, on cell surfaces, and at metallization elements. While weakened interfaces can delaminate and produce further paths for moisture ingress, shorting and corrosion of metallization can cause significant performance loss due to increased resistance. Modules hardly contain water after production, but internal moisture concentrations will rise over time in the field. The time to achieve the equilibrium moisture concentration level is one of the key parameters for the service lifetime of PV modules. It was estimated to be few days to a week in a breathable construction (glass/backsheet module), but up to a few years in an unbreathable construction (glass/glass module) [67].

3.1.4. Mechanical load

Various mechanical stresses can arise in PV modules due to manufacturing processes, transportation, handling during installation, wind, hail, snow, and thermo-mechanical loads. Since solar cells and metallization elements are thin and brittle, they are susceptible to such stress conditions and must be protected against cracking or fracture. Embrittled backsheets are also susceptible to mechanical loads. The front glass and the frame can also be damaged by mechanical loads which can lead to failure of the PV module. For polymeric packaging materials, mechanical stresses can create or extend cracks, in particular when the mechanical strength of a polymer is already weakened by other environmental stress factors such as UV light or humidity.

Depending on the orientation, modules often experience mechanical stresses on the front side during operation. Snow load is a static stress factor and long-term accumulation on the front side can exert significant force on the module which can cause cell cracks. If the module is tilted, snow accumulation and formation of ice on the module edge can induce bending forces and damage the rigidity of the frame. Even detachment of the frame from the module can occur [25]. In this case, modules lose their environmental and electrical protection. Wind, on the other hand, is a dynamic stress factor and can apply force on the front and the back depending on its direction. Mechanical loads due to wind can be significant as its direction and speed can change suddenly in gusty weather conditions. Prolonged exposure to cyclic gusty winds can cause cell micro-cracks to grow, and may induce fatigue failures of metallization elements [68]. Modules in the mounting structure should therefore be allowed some degree of twisting to withstand wind-induced vibrations.

3.1.5. Soiling

Soiling can arise from dust accumulation, air pollution, microbial algae growth, or bird droppings on the module surface. Uniform dust or biological soiling does not affect the long-term reliability of PV modules as opposed to other failure mechanisms such as corrosion, delamination, and cell cracks, but it can influence the power performance and this needs to be considered when measuring degradation outdoors. The degree of soiling can depend on the module surface properties, the location of the installation, and the mounting configuration of the modules such as tilt angle and height from ground. Dew formation or drying-out cycles can cause cementation of dust particles making them hard to remove by natural cleaning [49]. Dust soiling can be significant especially in desert climates [69]. On the other hand, in tropical climates with high humidity and frequent dew formation, biological soiling can also hinder the light transmission into the solar cell.

Bird dropping can be considered as a form of biological soiling, but its effect is different from dust and biological soiling. Because of their larger size and non-uniform formation on the front surface, they can block the light transmittance locally and thus can significantly affect the module performance and reliability [70]. This way they can act like partial shading of the module and lead to cell mismatch phenomena which would eventually result in hotspot formation unless cleaned. Hotspots are localized areas of elevated temperature, sometimes exceeding several hundreds of degrees. These are potentially one of the most severe types of module degradation because they can be dangerous and cause significant damage the solar cell and module packaging [71]. Hotspots form in areas where large currents pass through a small, resistive area, and can be caused by shading, soiling, and damaged cells or connections (metallization, interconnects) [72-75]. Whilst soiling can cause hotspots, there are a variety of other potential causes, and these are discussed further in section 4.

3.1.6. Chemicals (natural and industrial pollutants)

Some naturally occurring, or industrially produced, chemical species can cause corrosion of PV modules. The most common are salt mist in offshore areas (especially harmful in tropical climates), ammonia in agricultural rural areas, and sulfuric and nitric acid in industrial areas. These stress factors can degrade various components of the PV modules such as backsheets, adhesive edge sealants, junction boxes, wiring, and connectors. Besides performance degradation, they may cause safety issues due to impaired insulation of the modules.

3.2. Internal stress factors: processing and material incompatibility

In addition to environmental stress factors described before, internal factors like module design, bill of materials and processing related effects can also cause or influence module degradation. The lamination process has a big impact not only on quality, but also on reliability and long-term behaviour of PV modules [49,76,77]. Even though there are no substantial publications quantifying the relationship between quality and reliability of PV modules, qualitative descriptions on the effect of encapsulation quality on module reliability are available.

3.2.1. Processing

Poor processing, either in component or module manufacturing, is often identified as the root cause of PV module failures in the field. Some examples: thermal stressing during stringing and lamination can cause microcracks in solar cells [25,77]. Excessive thermal expansion of ethylene vinyl acetate (EVA) [78] during lamination may dislocate solar cells, increase the cell gaps and induce additional stress into the PV ribbon and the solder bonds [77]. Residual stress can be induced when the laminate is cooled down from the curing temperature of the encapsulant polymer to room temperature, and this can lead to warpage of the laminate [79]. One major reported issue is poor crosslinking of EVA, typically due to too low temperatures or too short crosslinking times [80-83]. Once installed, modules with a poor degree of crosslinking will eventually fully cure under operating conditions [83]. However, the availability of non-consumed peroxides has adverse effects on module reliability. Several studies reported higher susceptibility of modules with poorly crosslinked EVA towards PID and corrosion [61,80, 81,83]. Poorly crosslinked EVA was also found to be more prone to delamination, as it leads to insufficient adhesion strength between EVA and its adjacent module components (glass, cells and backsheet) [84-86].

3.2.2. Module architecture and bill of materials

Also, the module architecture and the bill of materials (BOM) affect degradation pathways and kinetics [49,87,88]. Availability of oxygen and water vapor, which play an important role in many degradation modes, strongly depends on the transport properties of the module packaging materials [89-92]. Physical properties of the packaging materials like water vapor transmission rates, oxygen transmission rates, acetic acid transmission rates, water solubilities, and film thicknesses are the key parameters for phenomena such as moisture ingress, acetic acid evaporation and oxidation [92]. In a breathable module construction with a backsheet film with a high water vapor transmission rate, moisture can move in and out of the module because of concentration gradients depending on the ambient relative humidity level and temperature during diurnal (and seasonal) cycles. Moisture in this case penetrates during the night when the temperature is low (and the relative humidity is high) and is released during the day when the temperature is high (and the relative humidity is low). A backsheet layer with a low (or zero) water vapor transmission rate, in an unbreathable construction as in glass/glass modules, can help prevent moisture ingress to some degree (since moisture can still penetrate from the sides), but it also keeps water vapor and other gaseous degradation by-products trapped inside the module which may cause further problems.

3.2.3. BOM incompatability

Design matching of relevant PV components, especially of the

encapsulant and backsheet with the rest of the module components, is therefore important for the durability and reliability of the module. Degradation modes influenced by the encapsulant and backsheet include discoloration, delamination, PID, snail trails and corrosion of metallization [49]. Also, the thermo-mechanical properties of the encapsulant (like the coefficient of thermal expansion, softening and damping behaviour) play an important role and must be balanced for a proper module design [49,61,93].

The first very prominent case of material incompatibility was yellowing of EVA, observed for PV modules which were installed in California in the early 1980s [93,94]. The discoloration has been found to be due to interactions between cross-linking peroxide and some stabilizing additives. A reformulation of the encapsulant with compatible additives has dramatically reduced this type of discoloration [94].

However, in recent years more cases of material incompatibilities have appeared, mostly due to the introduction of new materials into PV modules. Until 2010 most PV modules combined an EVA encapsulant and a fluoropolymer based backsheet with polyvinyl fluoride as outer layers, where the individual components were modified to enable proper adhesion. New encapsulant – backsheet combinations therefore require special attention. Many backsheets are optimized towards good adhesion to EVA. With new encapsulation films, e.g., based on polyolefins [95], common surface modifications may not have the intended effect. Also, certain combinations like polyethylene based encapsulants and polypropylene based backsheets may have adhesion issues [96,97]. Another example is the use of UV transparent encapsulants, which requires backsheets with UV stabilized inner layers in order to avoid backsheet degradation [98]. In relation to this, the influence of new encapsulant formulations on the corrosion of PV ribbons or the silver grid is poorly investigated so far, as well as the long-term behaviour of new solder materials on ribbons.

A special case with high impact has been the use of co-extruded backsheets based on polyamide. In recent years PV module failures with cracked polyamide backsheets occur more and more. The cracks appeared after several years of field aging but have never been observed after accelerated testing in the laboratory [99–102]. Two main types of polyamide backsheet-cracking were observed: tile-shaped, square cracks (along the intercellular spacings) and longitudinal cracks (beneath the busbars of the cells) [99]. The longitudinal cracks could be explained by deterioration of mechanical properties due to chemical and physical aging effects in combinations with thermo-mechanical stresses as the main driver for crack propagation [99,101]. For the squared cracks, however, a material incompatibility has been identified as the main root cause. The cracks are exclusively forming in conjunction with certain

Table 2

Common degradation and failure modes of PV module components and their effects. The delineation between degradation and failure is not always well defined.

termet.						
Degradation modes	Failure Modes	Effects				
Corrosion	Warpage	Increased risk of module damage				
Glass corrosion Breakage, soiling, Rec abrasion hot		Reduced current, hotspot formation				
Photo-	Discoloration,	Reduced current,				
oxidation	delamination	increased corrosion				
Corrosion	Fatigue, cracks	Reduced current, cell isolation, hotspot formation				
PID, LID, LETID	Cracks, cell	Reduced power,				
	isolation (cracks)	hotspot formation				
Photo-	Discoloration,	Increased				
oxidation,	delamination,	corrosion,				
hydrolysis	cracks	isolation failure				
-	Arcs,	Electrical fault,				
	delamination	detachment				
	Degradation modes Corrosion Glass corrosion Photo- oxidation Corrosion PID, LID, LETID Photo- oxidation, hydrolysis	Degradation modes Failure Modes Corrosion Warpage Glass corrosion Breakage, soiling, abrasion Photo- Discoloration, delamination Corrosion Fatigue, cracks PID, LID, LETID Cracks, cell isolation (cracks) Photo- Discoloration, delamination vidation, delamination, delamination, delamination, delamination, delamination				

EVA types which are prone to show degradation accompanied by significant acetic acid formation. A high concentration of acetic acid as well as the presence of a phosphate additive in the EVA correlated to stress cracking [99].

4. Degradation and failure modes

From the existing literature on PV reliability, degradation and failure modes can be identified that generally occur in photovoltaic technologies. In spite of the diversity of solar cell technologies, many of the module materials and components are identical or very similar. These elements include the module packaging, internal electrical circuit, bypass diodes, junction boxes, wiring and connectors, and frames. Table 2 connects the degradation phenomena and failure modes to the module component on one hand, and their effects on the PV system on the other. The upcoming subsections will treat each part of a PV module and its main degradation and failure problems.

4.1. Module packaging

Solar cells form just a small part of a PV module, as illustrated in Fig. 1; most of a module consists of packaging materials, including front and rear covers (glass, frontsheet, backsheet) and encapsulants. These fulfil several functions in a module, most importantly mechanical support, an optical couple, electrical insulation, and environmental protection. The role of packaging in photovoltaic energy generation is generally underestimated, as it does not play an active role in the power generation itself. However, the durability of module packaging is essential for long-term operation, and the choice of materials has a distinct impact on PV module attributes such as:

- Efficiency, as the optical properties of the module package determine the amount of light arriving at the solar cells;
- Quality, as the main early failures are caused by poor design and processing parameters, which are partly determined by the properties of the packaging components and material incompatibilities [25, 49,61,78,83,103];
- Reliability, as many PV module degradation modes are directly linked to packaging degradation and material interactions with it [49,61,104].

Module packaging degradation does not always lead to immediate performance losses, though many are suspected to have an impact on long-term performance, and therefore module lifetime. Besides performance losses, packaging failures may give rise to safety hazards, especially if the electrically insulating layers are compromised [105].

4.1.1. Glass

Low-iron soda-lime float glass is the most common superstrate or substrate material in PV modules because of its high transparency, good mechanical robustness, and low cost. Moreover, it is an excellent electrical insulator and impermeable to moisture and gases. It is most commonly used as a module front cover, and is also found increasingly for use as a back cover, especially in bifacial modules. The standard thickness is 3.2 mm, though other thicknesses may be used in particular applications such as bifacial and building-integrated PV.

4.1.1.1. Breakage. PV glass is commonly tempered or annealed to increase its strength, but nonetheless, the most common failure mode is breakage [25,49,106,107]. It has been found to account for up to a third of module field failures [26], though other reports mention a much lower occurrence [20,104,108]. Glass breakage can already happen during transportation or installation. It can also occur during operation because of thermal or mechanical stresses, such as from hotspots and static or dynamic loads. Frameless modules are additionally susceptible

to damage from edge impacts and improper clamping.

For c-Si modules, broken glass does not always have an immediate impact on performance and safety, because the cells, encapsulation and wiring can still be intact. Thin-film modules use a superstrate or substrate configuration with the solar cells deposited onto the glass, so broken glass is a more direct concern. In all cases, broken glass may cause cell or circuit damage that may generate hotspots, and it can also no longer act as an impermeable barrier to moisture or as an electrical insulator. Because of this it may accelerate degradation of the encapsulant and other components [109].

4.1.1.2. Coating erosion. PV glass is sometimes coated with antireflection or anti-soiling layers to improve overall module performance. Reflections off the surface of glass result in an optical loss of about 4% of incoming light, while soiling can cause optical losses of over 50% in some locations [108,110–112]. Anti-reflection and anti-soiling coatings are intended to minimize these losses, but they are subject to erosion over time, and thus lose their efficacy. This will reduce the output of a module, but it does not cause any safety hazards by itself.

4.1.2. Encapsulants

Solar cells are in direct contact with elastomeric materials called encapsulants. The most common encapsulation material today is a copolymer of ethylene and vinyl acetate (EVA). Historically, silicones (e. g. polydimethylsiloxane) and polyvinyl butyral were also used [19,93, 113]. However, the combination of low cost and decent properties – even if not the best – long made EVA the first choice in the PV market. Limitations of EVA and ever increasing demands on module performance and lifetime have led to the introduction of alternative encapsulation materials, most notably polyolefin elastomers, thermoplastic polyolefins, and ionomers [92,113].

The main degradation and failure modes of PV encapsulants include discolouration and delamination, such as in Fig. 5. Additionally, encapsulants are often partly responsible for degradation of other module components by facilitating or mediating degradation modes such as corrosion or potential induced degradation (PID) [25,61,104, 114,115].

4.1.2.1. Discoloration and delamination. Discoloration is directly related to the polymer films [18,80,93,116–120], and leads to light absorption in front of the cell, and therefore power losses. In most cases discolouration of the encapsulant is not attributed to photo-oxidation of the polymer chains themselves, but to the degradation of additives in the encapsulant. Discolouration was once a very common degradation mode, but in recent years encapsulants have been formulated with fewer or more stable additives, so its occurrence is much lower. Delamination is another relevant failure mode, and can occur at any interface within the laminate structure. Several factors affect adhesion strength, and physical and chemical aging processes of the encapsulants can promote delamination [86,121–123]. Though less common than discolouration by facilitating accumulation of moisture and degradation products.

4.1.2.2. Material interactions. More often, material interactions with the encapsulant are a root cause for PV module degradation. For example, acetic acid, which is a degradation product of EVA not only causes corrosion of the solar cell metallization and interconnects [25,49, 91,93,124–128], but also promotes PID and delamination [51,81, 129–131]. Furthermore it accelerates the oxidation process of EVA itself. In addition to acetic acid, which increases ion mobility, the PID effect is strongly affected by encapsulant properties like polarity, volume resistivity, and water vapor transmittance rate [51,61,114,132]. The permeation behaviour of encapsulant films also plays a significant role in corrosion processes, which are accelerated by the presence of water [133,134]. These problems with EVA are major limitations for



Fig. 5. Examples of encapsulant degradation and failure: discolouration (left; brownish haze) and delamination (right; lighter grey areas at the cell edges). Reproduced with permission from Refs. [18,25].

further improvements in module lifetime, and have motivated the development of alternative encapsulants [92,113,135,136].

4.1.3. Backsheets

The backside of a PV module is most often covered by a polymeric backsheet to provide electrical insulation and environmental protection. Alternatively, another layer of glass can be used to protect the backside, and there is ongoing discourse about the best architecture. Backsheets usually consist of a multilayer structure which is either laminated or coextruded, including an outer layer with good resistance to environmental stresses, an electrically insulating layer, and an inner layer with good adhesive properties. The outer layer (air-side) is commonly a fluoropolymer material, which is resistant to environmental degradation due to the strong carbon-fluorine bonds. Non-fluoropolymer alternatives are also in use, but they require stabilization, especially against UV light. The core layer is most often polyethylene terephthalate (PET) which has a high dielectric breakdown strength and mechanical stability. The inner layer (cell-side) is usually an EVA film, or another polymer with modified properties to improve adhesion. Typical fluoropolymers used in backsheet outer and inner layers include polyvinyl fluoride, polyvinilydene fluoride, and fluorethylene vinyl ether. Non-fluoropolymer alternatives for outer layers include materials such as PET, polyamide, and polyolefin, but there is a trade-off between the environmental stability and cost [63,137-139].

Degradation mechanisms and hence durability of the backsheet films differ depending on the specific backsheet structure and material formulations [63,137,140–146]. The most common degradation and failure modes observed during outdoor service are discolouration, chalking, delamination, and cracking, illustrated in Fig. 6. Several reports exist on the frequency of backsheet defects and failures, and while the reported ranges vary widely, they consistently appear as one of the most common PV module degradation modes [20,25,26,49,108,110].

4.1.3.1. Discoloration. Discolouration is mostly caused by photooxidative reactions during operation due to the formation of chemical degradation by-products called chromophores which give a yellow appearance [50,88,147–150]. White pigments such as TiO_2 and $BaSO_4$ are often added to polymer formulations because of their light absorbing properties which can increase the backsheet UV stability. However, degradation of the polymer surface on the air-side can cause these pigments to accumulate, which leads to gloss-loss and a chalky appearance [151–153]. Although both backsheet yellowing and chalking are not directly linked to module performance loss, their occurrence indicates chemical and morphological changes in the polymer structures and are early indicators of more serious forms of degradation such as embrittlement, cracking, and delamination.

4.1.3.2. Cracking. Backsheet cracking is a major problem found with increasing frequency [20,99–101,137,154,155]. Cracking impairs the electrical insulation and causes safety issues such as ground faults, current leakage, and reduced wet insulation resistance. It also opens new conduits for penetration of moisture and other chemicals into the module and thus facilitates degradation of other module components. After weathering, polymers have reduced molecular weight and increased crystallinity, which leads to embrittlement [99,104]. Cracks usually initiate at these weakened polymer chains and propagate in the presence of mechanical stresses. Therefore, in particular backsheet cracks that align with the gap between the cells and with metallization



Fig. 6. Examples of backsheet degradation and failure: discolouration (left), cracking (center), and delamination (right). Reproduced with permission from Refs. [25,99].

are critical. Cracking can be observed both on the cell-side and air-side, and crack patterns can vary depending on the material processing and exposure conditions [156].

4.1.3.3. Delamination. Delamination can occur at the backsheet/ encapsulant interface as well as between the layers of backsheet itself due to poor adhesion and lamination processes, or weather-induced degradation [86,109,157–162]. Delamination can be a cause for immediate concern for both performance and safety if it occurs at the module edge or near the junction box because it can result in current leakage or cause the box to detach. If delamination occurs at the module's center, it can elevate the thermal resistance and lead to a higher operating temperature for the cells in that area and act as a point for water condensation [163–165].

4.1.4. Frontsheets

As a frontside cover, polymeric sheets are sometimes used to replace glass, though they are less common than backsheets. Nonetheless, they are increasingly being used, especially in applications requiring light-weight and flexible module structures [166–168]. The materials for frontsheets are similar to those for backsheets, but they are not pigmented with mineral fillers for broadband light absorption because they must have high transparency. Instead, they are stabilized with chemical additives, including UV absorbers. The degradation modes described for backsheets are generally similar for frontsheets, however, in contrast with backsheets, discolouration and delamination will lead to immediate optical losses because of reduced light transmittance.

4.1.5. Edge seals

Both encapsulants and backsheets have some degree of permeability to moisture, so a PV module will become saturated with water after several months or years in the field [89,169]. Technologies which are especially sensitive to water (e.g. thin-film solar cells) sometimes have glass sheets both at the front and the back to ensure a long module lifetime. The weakest link for moisture ingress then becomes the edge sealant. Most edge sealants are based on desiccant-filled polyisobutylene [170–173].

In spite of their advantages, there are challenges in manufacturing modules with edge seals which has limited their adoption, and as such there is a lack of reports on their long-term performance. Edge sealing requires an additional process step prior to lamination. Moreover, edge seals are sensitive to glass edge pinching and they may prevent excess encapsulant from escaping a module during processing, leading to quality issues. Polyisobutylene edge seals are pigmented black for UV protection, and the material by itself is resistant to environmental degradation [170,172,173]. However, delamination can cause failure of the edge seal, especially in the presence of an external stress such as edge pinch.

4.2. Module internal circuitry

Solar cell metallization and interconnect wiring constitute the internal electrical circuit of a module laminate. Many failures or weaknesses in the circuit can occur because of design or processing factors, such as improper sizing or poor soldering quality [174–176]. Excluding such issues, the degradation of metallization and wiring is usually gradual and thus tends to have a delayed effect on performance. If the resistance of these components becomes too high, for example due to corrosion, hotspots and arcs may form which could pose safety concerns [25,26,49,109].

For crystalline silicon modules the front contact metallization layers (fingers and busbars) are usually made of a screen printed Ag-glass frit. Some emerging and high efficiency cell concepts utilize plating and additional metal layers for seeding, passivation, or improved contact resistance [177,178]. Rear contact metallization varies by cell

architecture, with Al, Ag, Ni, and Cu in use. For CIGS and CdTe front contact metallization is not common in commercial modules, and instead a transparent conducting oxide (TCO) serves as front contact. Some have suggested a TCO plus metal grid structures to improve module efficiencies, in which case Ni/Al, Al, and Cu are used [179,180]. For the back contact in CIGS solar cells, Mo is the industry standard, whereas for CdTe cells, ZnTe and Cu/Au, and Cu/C are common [181–183].

The purpose of solar cell and string interconnects is to connect cells or strings of cells in series. For crystalline silicon modules these are usually made from solder-coated copper ribbons, which are soldered onto the silver busbars. Pb–Sb and Pb–Sn–Ag solders are the most commonly used, though there is a push towards lead-free solders [184–186]. In thin-film module architectures a laser-based monolithic interconnection is standard, in which the various layers are patterned by laser ablation and the TCO acts as the interconnect [187,188]. Less commonly, ribbons or deposited metals are used as the interconnect material for thin-film solar cells, in a so-called grid assisted interconnection.

4.2.1. Corrosion, cracking, and contact failure

For all technologies, the metallization is susceptible to corrosion, cracking, and contact failure, shown in Fig. 7, and degradation of metallization appears as one of the most common field module failure modes [20,25,26,49,108,189–192]. The presence of moisture accelerates corrosion, and when an EVA encapsulant is used acetic acid is produced as it degrades, which poses an additional risk [91,93,125,126, 128]. For soldered and glued interconnects the joint is a weak point, because solders coarsen and phase separate over time, while adhesives become brittle [193,194]. This, in combination with corrosion and thermal cycling can cause fatigue failure [109,128,184,186,190, 195–197]. The impact of internal circuitry failure is severe because it reduces module performance and has a high risk of causing safety issues.

4.3. Solar cells

While the physics of failure for each PV absorber material (e.g. silicon, CIGS, CdTe, CdS) is unique, there are some general degradation modes which can affect all of them, including cell cracking, hotspots, light induced degradation (LID), and potential induced degradation (PID). Cell defects and degradation are among the most commonly reported module defects in the field, but are not always readily detected by simple inspection.

4.3.1. Cell cracking

Many semiconductors are brittle, so cell cracking is a concern for PV modules [198,199]. Cell cracks can be initiated during manufacturing due to residual stresses from thermal processing, soldering, and lamination [200–203]. They can also arise during transportation and installation, and from static or cyclic mechanical loads during operation [106,107,204]. Depending on the number and size of cracks, module power may be only slightly affected, or hotspots and dead areas may form. However, once present their severity is likely to increase over time due to mechanical or thermomechanical stresses, which would open and propagate cracks [201,205–208]. Thin-film solar cells are less susceptible to cracking, because strain levels are comparatively lower than for silicon solar cells. Nonetheless, damage to the glass superstrate or substrate may cause cell cracks.

4.3.2. Hotspots

As discussed, hotspots are cell areas of elevated temperatures, which can potentially cause severe module degradation and accelerate the formation and propagation of other failure mechanisms [71]. Hotspots form in areas where large currents pass through resistive areas, and can be caused by shading, soiling, and damaged cells or connections (metallization, interconnects) [71,209,210].



Fig. 7. Examples of degradation and failure of the internal electrical circuit, including corrosion (left: discoloration visible on the string interconect ribbon) and fatigue cracking (right: broken interconnect ribbon between cells). Reproduced with permission from Ref. [49].

4.3.3. Light induced degradation (LID)

Light induced degradation (LID) is a power degradation effect which occurs during the initial stabilization of a PV module when exposed to light. It affects practically all module technologies, though the effect is typically small, resulting in a loss of up to 5% of module power. Because of its ubiquity and predictability the name-plate power ratings of modules already take these losses into account [25]. The mechanism of LID involves metastabilities in the semiconductor layers present from high temperature processing or diffusion between layers [211,212].

4.3.4. Potential induced degradation (PID)

In recent years potential induced degradation (PID) has been identified as a major concern in field modules [25,49,108,115]. This occurs when there is a high electrical potential between the module frame and solar cells, which generates leakage currents through the module packaging and drives cations (notably sodium) from the glass into the solar cell, TCO, or anti-reflective coatings [51,81,115,129–132]. PID leads to enhanced recombination and shunt formation, and in thin-film modules it can also lead to TCO corrosion and p-n junction damage. The PID effect can lead to significant power losses, and is more severe on the negative pole of a string. PID can be mitigated by use of modified anti-reflective coatings, high volume resistivity encapsulants, Na-free glass or Na diffusion barriers, or alternative inverter configurations [51,114,115,132,213–215].

4.4. Other components

4.4.1. Bypass diodes

Bypass diodes are protective components intended to minimize module losses during reverse bias operation by providing a path for the current of good cells to bypass bad cells. When there is a large mismatch in short-circuit current between several cells, the cell or cells with lowest current may become reverse biased and then overheat. This can occur temporarily during shading or permanently when a cell or the internal electric circuit is compromised.

Bypass diodes are usually integrated into the junction box, and are a somewhat common source of issues in underperforming or failed modules [25,108,110,216–220]. Catastrophic failure modes of bypass diodes include arcing, electrostatic discharge, and thermal runaway, and can lead to severe performance losses as well as safety problems [25,108, 221–226]. Electrostatic discharge occurs when a large current passes through the diode over a short period of time, which can occur due to a lightning strike or during manufacturing if there are inadequate electrostatic discharge protections in place. Thermal runaway happens when there is insufficient heat dissipation, which results in more current passing through the diode, and consequently higher temperatures. This runaway process continues until the temperature is high enough to destroy the diode. Aside from these catastrophic failures, gradual degradation of bypass diodes can occur due to continuous high temperature operation or thermal cycling. In both cases excessive temperatures and temperature excursions degrade the semiconductor junction and contacts, ultimately resulting in their failure [223].

4.4.2. Junction box

The junction box is typically located on the backside of a PV module, and less commonly on the edge. It protects the connections of the strings, external wiring, and often the bypass diodes. The box is typically made from polycarbonate, and adhered to the backside of the module. In documented module field failures the junction box is a fairly common problem [25,26,49,108,110,227–229]. The main failure modes for junction boxes include detachment (from the module backsheet), poorly sealed or closed boxes, corrosion, and arcing due to bad or degraded wiring. Degradation and failure of junction box components can lead to major performance losses and safety hazards because of the high current levels passing through [25,26,108].

4.4.3. Frame

The majority of commercial modules are framed to protect the edges of the glass and provide module mounting points. Anodised aluminum is the most common frame material, because of its high strength, low weight, and low cost. Frames can become loosened, deformed, or corroded over time [25,192]. These can be caused or accelerated either by poor manufacturing quality or mechanical loading. Degradation of the frame is less common than most of the other failures modes described in this section [108,110]. Nonetheless, because it serves as a mounting point for modules, its weakness or failure can increase the likelihood of cell damage or module failure, especially in conditions of strong mechanical loading (e.g. wind or hurricane) [230].

4.5. Overview of complexity

The interplay of stressors on component and resultant failure mecanisms and their effects on module functioning is complex. The same stressor can act upon multiple components, leading to multiple failure modes. Also, some failure modes also result in new stressors (e.g. a failure that allows water to ingress will result in a new stressor of corrosion). Fig. 8 serves as an aid so as to obtain a clear view of this complex interplay.

5. Summary of reliability challenges and future perspective

As shown in section 3, PV modules are exposed to various external (environmental conditions) and internal stress factors (processing, module architecture, bill of materials) that influence their performance and long-term reliability. In the rarest cases PV module failures are related to just one single stress but usually an effect occurs due to multiple combined stresses [25,231]. This complex stress situation however is usually not reflected in accelerated indoor aging testing, where samples are exposed to single stresses. Especially failure modes that include thermo-mechanical stresses or electrical potentials were not



Fig. 8. Flow diagram representing the relationships between stressor, component, failure and effect. Lines are coloured to discern line crossings. Thick black lines to the left of the "component" and "effect" are there to indicate the termination of the connector from the previous point in the flow diagram. Thick coloured lines to the right indicate branching. Dotted lines indicate when failure results in a new stressor.

induced by traditionally used single stress tests. In the past this has led to unexpected degradation mechanisms several years after field deployment of PV modules, which were not previously foreseen in laboratory accelerated testing, such as PID [51] LeTID [53,232] and backsheet cracking [99,100,233]. In all cases, after a first description of the failure modes an analysis was executed, trying to identify the main stress factors, as well as the chemical and physical degradation mechanisms leading to the failure modes. Consequently, new accelerated test setups have been developed in order to trigger these specific failure modes, such as, for instance, PID tests on cell and modules level or the solder bump test developed for backsheet cracking [234].

A more recent approach is the development and implementation of so-called agnostic stress tests that try to replicate the complex stress situation as well as possible. These tests either rely on the sequential or combined exposure to multiple stresses [56,57,235,236]. In both cases failure modes like backsheet cracking [237] have successfully been triggered. To summarize this review, Fig. 8 shows potential relationships between stressors, components, failures and effects on the basis of our findings. The body of experimental data and field studies shows that there are a number of stressors that impact upon multiple parts of a PV module. A key effort to support future reliability work would be to understand which degradation mechanisms have the greatest impact in the field. Challenges exist with this as the dominant failure mechanism is likely to be influenced by the specific situation on location, manufacturing control, module type, vintage and bill of materials. Such studies will be a complex piece of work however utterly useful for the PV

research community and essential for the development of reliable PV modules for various markets.

So, what is the main lesson for deployment of future PV technologies, and where are the research gaps? The current PV market shows an extremely high-cost pressure, which is also the driving factor for the development and implementation of new module designs and the use of new materials and components. New technologies, which promise either higher efficiency for the same cost or cost reduction at same efficiency, are very often quickly introduced to the market [30,238]. Moreover, the process of material innovation for PV is further complicated by the complex interactions within a PV module. The advantage of one material may be outweighed by its interaction with another component. For example, EVA is inexpensive and highly effective for encapsulation, however it degrades to form acetic acid which can cause corrosion of the metallization if it is not allowed to escape the module package due to use of an impermeable backsheet. New materials must work within the whole module package and in concert with the other materials present [238]. With current production capacities, many Gigawatts of modules with new technologies and materials can be produced and installed without having sufficient experience about long term reliability. This presents a technology risk for the industry.

However, proper material selection and comprehensive knowledge of material properties combined with suitable qualification and reliability testing exceeding current test protocols or IEC standards can help to minimize these risks. It is clear that future research is needed on new materials and module design changes as they are introduced. The bottom line is that each module design or material combination has to be tested and qualified individually. Moreover, agnostic combined stress tests need to be used, so that also unknown, new failure modes related specific designs or BOMS may be triggered during the development phase. Standardization of such agnostic stress tests will be instrumental in the further development of long-lifetime modules and the necessary market acceptance and appreciation of long-lifetime claims.

A future research gap is to consider the impact of performance, cost and reliability on the PV module sustainability. Greater research in this direction is needed as sustainability has long been an afterthought in PV research driven by cost reduction. As we have surpassed the point of grid parity and the module price is only a smaller fraction of the overall system cost, price differentiation becomes an option for longer-lifetime modules. It is worth stressing that through increased reliability and higher lifetime of PV modules, a significant impact on sustainability and economics is achieved. A recent study showed that module stability becomes more important for economic evaluation and that inferior stability cannot be compensated by lower module prizes but only by much higher efficiency [239]. Longer lifetimes would also reduce the environmental impact of photovoltaics, as they reduce the number of modules that need to be produced for replacement and consequently also PV waste. To give a rough estimation, improving the service life of a PV module from 25 to 40 years saves about 130 GW/year of new modules, that do not need to be produced and 7 million tons/year of PV panel waste, that does not require recycling. In addition, 'Design for Recycling, Repair or Reuse' might become a greater research area and design challenge. However, as designs and materials are changed, a strong understading of module reliability will still be needed and many of the testing/failure modes.

6. Conclusions

This review article has presented an overview of the state-of-the-art knowledge on the reliability of PV modules and their degradation mechanisms. The most common technology today is mono- and multicrystalline silicon, but this article aims to give a generic summary which is relevant for a wider range of photovoltaic technologies including thin-film devices. Initially definitions for reliability and quality and testing standards were reviewed. Subsequently the primary stress factors that affect module degradation were summarised; this includes irradiance, temperature, moisture, mechanical stress, soiling and chemicals. Finally, common degradation and failure modes were identified that occur generically in photovoltaic technologies were reviewed. Many PV technologies consist of similar architectures in terms of the module materials and components. These elements include the module packaging, internal electrical circuit, bypass diodes, junction boxes, wiring and connectors, and frames. The dominant degradation phenomena and failure modes in all module components were summarised. Quality and reliability testing has come to a stage where the durability of each component under a single stress can be predicted well, but accurate reliability estimations for a combination of materials under a combination of time-varying stresses remain challenging. Building on this knowledge, strategies to improve the operational lifetime of PV systems and thus, to reduce the electricity cost and improve the sustainability can be devised and lifetimes of PV modules can be extended.

Declaration of competing interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgement

This review article is based upon work from COST Action CA16235 PEARL PV, WG2, supported by COST (European Cooperation in Science and Technology). COST is a funding agency for research and innovation networks. Our Actions help connect research initiatives across Europe and enable scientists to grow their ideas by sharing them with their peers. This boosts their research, career and innovation.

References

- Gielen D, Gorini R, Leme R, Prakash G, Wagner N, Janeiro L, et al. World energy transitions outlook: 1.5° C pathway. 2021.
- [2] Solar Skins. An opportunity for greener cities. SolarPower Eur ETIP PV; 2019.
 [3] Aghaei M, Kettle J, Reinders A. Reliability and durability research activities of PV
- modules, components and systems in cost action pearl PV 2020.
- 4] Philips D, Warmuth W. Photovoltaics report. Fraunhofer ISE and PSE; 2021.
- [5] Green MA, Dunlop ED, Hohl-Ebinger J, Yoshita M, Kopidakis N, Ho-Baillie AWY. Solar cell efficiency tables (Version 57). Prog Photovoltaics Res Appl 2021;29: 3–15. https://doi.org/10.1002/pip.3228.
- [6] NREL Best Research-Cell Efficiency Chart n.d. https://www.nrel.gov/pv/cellefficiency.html.
- [7] Richter S, Werner M, Swatek S, Hagendorf C. Understanding the snail trail effect in silicon solar modules on microstructural scale. 27th Eur Photovolt Sol Energy Conf Exhib 2012. https://doi.org/10.4229/27thEUPVSEC2012-4BV.3.7.
- [8] Pearson GL. Conversion of solar to electrical energy. Am J Phys 1957;25:591–8.
 [9] Kato N, Takeda Y, Higuchi K, Takeichi A, Sudo E, Tanaka H, et al. Degradation analysis of dye-sensitized solar cell module after long-term stability test under outdoor working condition. Sol Energy Mater Sol Cells 2009;93:893–7. https:// doi.org/10.1016/j.solmat.2008.10.022.
- [11] Ludin NA, Mustafa NI, Hanafiah MM, Ibrahim MA, Asri Mat Teridi M, Sepeai S, et al. Prospects of life cycle assessment of renewable energy from solar photovoltaic technologies: a review. Renew Sustain Energy Rev 2018. https:// doi.org/10.1016/j.rser.2018.07.048.
- [12] Carlé JE, Helgesen M, Hagemann O, Hösel M, Heckler IM, Bundgaard E, et al. Overcoming the scaling lag for polymer solar cells. Joule 2017;1:274–89. https:// doi.org/10.1016/j.joule.2017.08.002.
- [13] Soares GA, David TW, Anizelli H, Miranda B, Rodrigues J, Lopes P, et al. Outdoor performance of organic photovoltaics at two different locations: a comparison of degradation and the effect of condensation. J Renew Sustain Energy 2020;12: 63502.
- [14] Fu Z, Xu M, Sheng Y, Yan Z, Meng J, Tong C, et al. Encapsulation of printable mesoscopic perovskite solar cells enables high temperature and long-term outdoor stability. Adv Funct Mater 2019:29:1809129.
- [15] Archer MD, Green MA. Clean electricity from photovoltaics, vol. 4. World Scientific; 2014.
- [16] Ramanujam J, Bishop DM, Todorov TK, Gunawan O, Rath J, Nekovei R, et al. Flexible CIGS, CdTe and a-Si: H based thin film solar cells: a review. Prog Mater Sci 2020;110:100619.
- [17] O'Connor P, Kleyner A. Practical reliability engineering. John Wiley & Sons; 2012.
- [18] Annigoni E, Virtuani A, Caccivio M, Friesen G, Chianese D, Ballif C. 35 years of photovoltaics: analysis of the TISO-10-kW solar plant, lessons learnt in safety and

M. Aghaei et al.

Renewable and Sustainable Energy Reviews 159 (2022) 112160

performance—Part 2. Prog Photovoltaics Res Appl 2019;27:760–78. https://doi. org/10.1002/pip.3146.

- [19] Virtuani A, Caccivio M, Annigoni E, Friesen G, Chianese D, Ballif C, et al. 35 years of photovoltaics: analysis of the TISO-10-kW solar plant, lessons learnt in safety and performance—Part 1. Prog Photovoltaics Res Appl 2019;27:328–39. https:// doi.org/10.1002/pip.3104.
- [20] DuPont global PV reliability: 2020 Field analysis. https://skypower.com/wp-co ntent/uploads/2020/08/Global-Field-Reliability-Report-2020.pdf; 2020.
- [21] 61215 IEC. Terrestrial photovoltaic (PV) modules-design qualification and type approval. 2016.
- [22] Verlinden P, Sark W v. List of international standards related to PV. In: Reinders AHME, Sark Wv, Verlinden PJ, Freundlich A, editors. Photovolt. Sol. Energy from fundam. To appl. Wiley Online Library; 2017. p. 658–71.
- [23] Alhmoud L, Wang B. A review of the state-of-the-art in wind-energy reliability analysis. Renew Sustain Energy Rev 2018;81:1643–51.
- [24] Kettle J, Stoichkov V, Kumar D, Corazza M, Gevorgyan SA, Krebs FC. Using ISOS consensus test protocols for development of quantitative life test models in ageing of organic solar cells. Sol Energy Mater Sol Cells 2017;167:53–9.
- [25] Köntges M, Kurtz S, Packard CE, Jahn U, Berger K, Kato K, et al. Review of failures of photovoltaic modules. 2014. https://doi.org/978-3-906042-16-9.
- [26] Degraaff D, Lacerda R, Campeau Z, Corp S. Degradation mechanisms in Si module technologies observed in the field; their analysis and statistics. In: 2011 photovolt modul reliab work. NREL; 2011.
- [27] Short W, Packey DJ, Holt T. A manual for the economic evaluation of energy efficiency and renewable energy technologies. Golden, CO (United States): National Renewable Energy Lab.; 1995.
- [28] Campbell M. The economics of PV systems. In: Reinders AHME, Sark Wv, Verlinden PJ, Freundlich A, editors. Photovolt. Sol. Energy from fundam. To appl. Wiley Online Library; 2016. p. 621–33.
- [29] Ray D. Lazard's levelized cost of energy analysis—version 13.0. New York, NY, USA: Lazard; 2019. p. 20.
- [30] International Technology Roadmap for Photovoltaic (ITRPV). Vdma. Germany: Frankfurt Am Main; 2019.
- [31] Vartiainen E, Masson G, Breyer C, Moser D, Román Medina E. Impact of weighted average cost of capital, capital expenditure, and other parameters on future utility-scale PV levelised cost of electricity. Prog Photovoltaics Res Appl 2020;28: 439–53.
- [32] Tjengdrawira C, Richter M. 03 review and gap analyses of technical assumptions in PV electricity cost. Report on current practices in how technical assumptions are accounted in PV investment cost. Sol Bankability Proj 2016.
- [33] Adinolfi G, Agostinelli G, Moser D, et al. PV quality and economy. PhotoVoltaic European Technology & Innovation Platform; 2018. https://doi.org/10.13140/ RG.2.2.23510.50244.
- [34] Fthenakis V. Life cycle assessment of photovoltaics. In: Reinders AHME, Sark Wv, Verlinden PJ, Freundlich A, editors. Photovolt. Sol. Energy. Wiley Online Library; 2016. p. 646–57.
- [35] Simon P. Photovoltaics report. Freiburg, Fraunhofer ISE; 2019.
- [36] Wirth H. Recent facts about photovoltaics in Germany. Fraunhofer Institute for Solar Energy, Photovoltaic Modules and Power Plants; 2021.
- [37] Luo W, Khoo YS, Kumar A, Low JSC, Li Y, Tan YS, et al. A comparative life-cycle assessment of photovoltaic electricity generation in Singapore by multicrystalline silicon technologies. Sol Energy Mater Sol Cells 2018;174:157–62.
- [38] Rajput P, Malvoni M, Manoj Kumar N, Sastry OS, Jayakumar A. Operational performance and degradation influenced life cycle environmental–economic metrics of mc-Si, a-Si and HIT photovoltaic arrays in hot semi-arid climates. Sustainability 2020;12:1075.
- [39] Fthenakis V, Leccisi E. Updated sustainability status of crystalline silicon-based photovoltaic systems: life-cycle energy and environmental impact reduction trends. Prog Photovoltaics Res Appl 2021.
- [40] Jordan DC, Kurtz SR, VanSant K, Newmiller J. Compendium of photovoltaic degradation rates. Prog Photovoltaics Res Appl 2016. https://doi.org/10.1002/ pip.2744.
- [41] Phinikarides A, Kindyni N, Makrides G, Georghiou GE. Review of photovoltaic degradation rate methodologies. Renew Sustain Energy Rev 2014. https://doi. org/10.1016/j.rser.2014.07.155.
- [42] Jordan DC, Kurtz SR. The dark horse of evaluating long-term field performance-Data filtering. IEEE J Photovoltaics 2014. https://doi.org/10.1109/ JPHOTOV.2013.2282741.
- [43] Jordan DC, Kurtz SR. Analytical improvements IN PV degradation rate determination. Conf Rec IEEE Photovolt Spec Conf 2010. https://doi.org/ 10.1109/PVSC.2010.5617074.
- [44] Kyprianou A, Phinikarides A, Makrides G, Georghiou GE. Definition and computation of the degradation rates of photovoltaic systems of different technologies with robust principal component analysis. IEEE J Photovoltaics 2015;5:1698–705.
- [45] Phinikarides A, Makrides G, Zinsser B, Schubert M, Georghiou GE. Analysis of photovoltaic system performance time series: seasonality and performance loss. Renew Energy 2015;77:51–63.
- [46] Hasselbrink E, Anderson M, Defreitas Z, Mikofski M, Shen YC, Caldwell S, et al. Validation of the PVLife model using 3 million module-years of live site data. Conf Rec IEEE Photovolt Spec Conf 2013. https://doi.org/10.1109/ PVSC.2013.6744087.
- [47] Cronin A, Pulver S, Cormode D, Jordan D, Kurtz S, Smith R. Measuring degradation rates of PV systems without irradiance data. Prog Photovoltaics Res Appl 2014;22:851–62.

- [48] Richter E, Schmidt MT, Kalisch J, Woyte A, de Brabandere K, Lorenz M. Uncertainties in PV modelling and monitoring. 31st Eur. Photovolt. Sol. Energy Conf. Exhib. 2015:1683–91.
- [49] Köntges M, Oreski G, Jahn U, Herz M, Hacke P, Weiss K-A, et al. Assessment of photovoltaic module failures in the field. 2017.
- [50] Gambogi W, Heta Y, Hashimoto K, Kopchick J, Felder T, MacMaster S, et al. A comparison of key PV backsheet and module performance from fielded module exposures and accelerated tests. IEEE J Photovoltaics 2014. https://doi.org/ 10.1109/JPHOTOV.2014.2305472.
- [51] Pingel S, Frank O, Winkler M, Oaryan S, Geipel T, Hoehne H, et al. Potential induced degradation of solar cells and panels. Conf Rec IEEE Photovolt Spec Conf 2010. https://doi.org/10.1109/PVSC.2010.5616823.
- [52] Hacke P, Terwilliger K, Glick S, Trudell D, Bosco N, Johnston S, et al. Test-tofailure of crystalline silicon modules. Conf Rec IEEE Photovolt Spec Conf 2010. https://doi.org/10.1109/PVSC.2010.5614472.
- [53] Kersten F, Engelhart P, Ploigt HC, Stekolnikov A, Lindner T, Stenzel F, et al. A new mc-Si degradation effect called LeTID. IEEE 42nd Photovolt. Spec. Conf. PVSC 2015. https://doi.org/10.1109/PVSC.2015.7355684. 2015.
- [54] Stoichkov V, Kumar D, Tyagi P, Kettle J. Multistress testing of OPV modules for accurate predictive aging and reliability predictions. IEEE J Photovoltaics 2018. https://doi.org/10.1109/JPHOTOV.2018.2838438.
- [55] Hartman K, Hacke P, Owen-Bellini M, Jin Y, Cummings M, Taylor A, et al. Validation of advanced photovoltaic module materials and processes by combined-accelerated stress testing (C-ast). Conf Rec IEEE Photovolt Spec Conf 2019. https://doi.org/10.1109/PVSC40753.2019.8980545.
- [56] Gambogi W, Yu B-L, Felder T, MacMaster S, Choudhury KR, Tracy J, et al. Development of accelerated test sequences to assess long term durability of PV modules. In: 2019 IEEE 46th photovolt. Spec. Conf. IEEE; 2019. p. 2406–10.
- [57] Owen-Bellini M, Hacke P, Miller DC, Kempe MD, Spataru S, Tanahashi T, et al. Advancing reliability assessments of photovoltaic modules and materials using combined-accelerated stress testing. Prog Photovoltaics Res Appl 2021;29:64–82.
- [58] Theelen M, Bakker K, Steijvers H, Roest S, Hielkema P, Barreau N, et al. In situ monitoring of the accelerated performance degradation of solar cells and modules: a case study for Cu (in, Ga) Se2 solar cells. J Vis Exp JoVE 2018.
- [59] Kurtz S. Advance solar technology by marrying quality assurance with design engineering. Nat Energy 2018;3:1016–8.
- [60] ASTM International. ASTM g173-03(2012), standard tables for reference solar spectral irradiances: direct normal and hemispherical on 37° tilted surface. 2012. West Conshohocken, PA.
- [61] Oreski G, Ottersböck B, Omazic A. Degradation processes and mechanisms of encapsulants. In: Durab. Reliab. Polym. Other mater. Photovolt. Modul. Elsevier; 2019. p. 135–52. https://doi.org/10.1016/B978-0-12-811545-9.00006-9.
 [62] Exposure data - solar and ultraviolet radiation. 1992. Lyon (FR).
- [63] Exposure data 'solar and untavore radiation. 1992. Byon (11).
 [63] Fairbrother A, Phillips N, Gu X. Degradation processes and mechanisms of backsheets. In: Durab. Reliab. Polym. Other mater. Photovolt. Modul. Elsevier; 2019. https://doi.org/10.1016/B978-0-12-811545-9.00007-0. 153-74.
- [64] Arrhenius S. Über die Dissociationswärme und den Einfluss der Temperatur auf den Dissociationsgrad der Elektrolyte. Z Phys Chem 1889;4:96–116.
- [65] Eitner U, Köntges M, Brendel R. Measuring thermomechanical displacements of solar cells in laminates using digital image correlation. Conf Rec IEEE Photovolt Spec Conf 2009. https://doi.org/10.1109/PVSC.2009.5411248. 001280–4.
- [66] Zielnik AF, Burns DM. Service life prediction of PV materials. In: Durab. Reliab. Polym. Other mater. Photovolt. Modul. Elsevier; 2019. p. 297–328. https://doi. org/10.1016/B978-0-12-811545-9.00013-6.
- [67] Kempe MD. Modeling of rates of moisture ingress into photovoltaic modules. Sol Energy Mater Sol Cells 2006;90:2720–38. https://doi.org/10.1016/j. solmat.2006.04.002.
- [68] Kilikevičius A, Čereška A, Kilikevičiene K. Analysis of external dynamic loads influence to photovoltaic module structural performance. Eng Fail Anal 2016;66: 445–54. https://doi.org/10.1016/j.engfailanal.2016.04.031.
- [69] Cordero RR, Damiani A, Laroze D, MacDonell S, Jorquera J, Sepúlveda E, et al. Effects of soiling on photovoltaic (PV) modules in the Atacama Desert. Sci Rep 2018;8:1–14. https://doi.org/10.1038/s41598-018-32291-8.
- [70] Sisodia AK, kumar Mathur R. Impact of bird dropping deposition on solar photovoltaic module performance: a systematic study in Western Rajasthan. Environ Sci Pollut Res 2019;26:31119–32. https://doi.org/10.1007/s11356-019-06100-2.
- [71] Kato K. In: Dhere NG, Wohlgemuth JH, Lynn KW, editors. PVRessQl: a research activity on reliability of PV systems from an user's viewpoint in Japan; 2011. 81120K. https://doi.org/10.1117/12.896135.
- [72] Wang A, Xuan Y. Close examination of localized hot spots within photovoltaic modules. Energy Convers Manag 2021;234:113959.
- [73] Tang S, Xing Y, Chen L, Song X, Yao F. Review and a novel strategy for mitigating hot spot of PV panels. Sol Energy 2021;214:51–61.
- [74] Clement CE, Singh JP, Birgersson E, Wang Y, Khoo YS. Hotspot development and shading response of shingled PV modules. Sol Energy 2020;207:729–35.
- [75] Ahsan S, Niazi KAK, Khan HA, Yang Y. Hotspots and performance evaluation of crystalline-silicon and thin-film photovoltaic modules. Microelectron Reliab 2018;88:1014–8.
- [76] Davis KO, Rodgers MP, Scardera G, Brooker RP, Seigneur H, Mohajeri N, et al. Manufacturing metrology for c-Si module reliability and durability Part II: cell manufacturing. Renew Sustain Energy Rev 2016. https://doi.org/10.1016/j. rser.2015.12.217.
- [77] Schneller EJ, Brooker RP, Shiradkar NS, Rodgers MP, Dhere NG, Davis KO, et al. Manufacturing metrology for c-Si module reliability and durability Part III:

Renewable and Sustainable Energy Reviews 159 (2022) 112160

module manufacturing. Renew Sustain Energy Rev 2016. https://doi.org/10.1016/j.rser.2015.12.215.

- [78] Knausz M, Oreski G, Schmidt M, Guttmann P, Berger K, Voronko Y, et al. Thermal expansion behavior of solar cell encapsulation materials. Polym Test 2015;44: 160–7. https://doi.org/10.1016/j.polymertesting.2015.04.009.
- [79] Dietrich S, Pander M, Sander M, Schulze SH, Ebert M. Mechanical and thermomechanical assessment of encapsulated solar cells by finite-elementsimulation. In: Dhere NG, Wohlgemuth JH, Lynn K, editors. Reliab. Photovolt. Cells, modul. Components, vol. 7773. SPIE; 2010. 77730F. https://doi.org/ 10.1117/12.860661. Syst. III.
- [80] Morlier A, Klotz S, Sczuka S, Kunze I, Schaumann I, Blankemeyer S, et al. Influence of the curing state of ethylene-vinyl acetate on photovoltaic modules aging. 28th. EUPVSEC; 2013.
- [81] Jonai S, Hara K, Tsutsui Y, Nakahama H, Masuda A. Relationship between crosslinking conditions of ethylene vinyl acetate and potential induced degradation for crystalline silicon photovoltaic modules. Jpn J Appl Phys 2015;54:8KG01. https://doi.org/10.7567/JJAP.54.08KG01. Japan Society of Applied Physics.
- [82] Kempe MD, Miller DC, Wohlgemuth JH, Kurtz SR, Moseley JM, Shah Q, et al. A field evaluation of the potential for creep in thermoplastic encapsulant materials. Conf Rec IEEE Photovolt Spec Conf 2012. https://doi.org/10.1109/ PVSC.2012.6317958.
- [83] Oreski G, Rauschenbach A, Hirschl C, Kraft M, Eder GC, Pinter G. Crosslinking and post-crosslinking of ethylene vinyl acetate in photovoltaic modules. J Appl Polym Sci 2017;134. https://doi.org/10.1002/app.44912.
- [84] Kuitche JM, Pan R, Tamizhmani G. Investigation of dominant failure mode(s) for field-aged crystalline silicon PV modules under desert climatic conditions. IEEE J Photovoltaics 2014;4:814–26. https://doi.org/10.1109/ JPHOTOV.2014.2308720.
- [85] Matsuda K, Watanabe T, Sakaguchi K, Yoshikawa M, Doi T, Masuda A. Microscopic degradation mechanisms in silicon photovoltaic module under longterm environmental exposure. Jpn J Appl Phys 2012. https://doi.org/10.1143/ JJAP.51.10NF07.
- [86] Novoa FD, Miller DC, Dauskardt RH. Adhesion and debonding kinetics of photovoltaic encapsulation in moist environments: adhesion and debonding kinetics of photovoltaic encapsulation. Prog Photovoltaics Res Appl 2016;24: 183–94. https://doi.org/10.1002/pip.2657.
- [87] French RH, Podgornik R, Peshek TJ, Bruckman LS, Xu Y, Wheeler NR, et al. Degradation science: mesoscopic evolution and temporal analytics of photovoltaic energy materials. Curr Opin Solid State Mater Sci 2015. https://doi. org/10.1016/j.cossms.2014.12.008.
- [88] Gok A, Fagerholm CL, French RH, Bruckman LS. Temporal evolution and pathway models of poly(ethylene-terephthalate) degradation under multi-factor accelerated weathering exposures. PLoS One 2019;14:1–22. https://doi.org/ 10.1371/journal.pone.0212258.
- [89] Hülsmann P, Weiss KA. Simulation of water ingress into PV-modules: IEC-testing versus outdoor exposure. Sol Energy 2015;115:347–53. https://doi.org/10.1016/ j.solener.2015.03.007.
- [90] Hülsmann P, Weiß KA, Köhl M. Temperature-dependent water vapour and oxygen permeation through different polymeric materials used in photovoltaic-modules. Prog Photovoltaics Res Appl 2014. https://doi.org/10.1002/pip.2273.
- [91] Kempe MD, Jorgensen GJ, Terwilliger KM, McMahon TJ, Kennedy CE, Borek TT. Acetic acid production and glass transition concerns with ethylene-vinyl acetate used in photovoltaic devices. Sol Energy Mater Sol Cells 2007;91:315–29. https:// doi.org/10.1016/j.solmat.2006.10.009.
- [92] Oreski G, Mihaljevic A, Voronko Y, Eder GC. Acetic acid permeation through photovoltaic backsheets: influence of the composition on the permeation rate. Polym Test 2017;60:374–80. https://doi.org/10.1016/j. polymertesting 2017 04 025
- [93] Czanderna AW, Pern FJ. Encapsulation of PV modules using ethylene vinyl acetate copolymer as a pottant: a critical review. Sol Energy Mater Sol Cells 1996; 43:101–81. https://doi.org/10.1016/0927-0248(95)00150-6.
- [94] Klemchuk P, Ezrin M, Lavigne G, Holley W, Galica J, Agro S. Investigation of the degradation and stabilization of EVA-based encapsulant in field-aged solar energy modules. Polym Degrad Stabil 1997;55:347–65. https://doi.org/10.1016/S0141-3910(96)00162-0.
- [95] Oreski G, Omazic A, Eder GC, Voronko Y, Neumaier L, Mühleisen W, et al. Properties and degradation behaviour of polyolefin encapsulants for photovoltaic modules. Prog Photovoltaics Res Appl 2020. https://doi.org/10.1002/pip.3323.
- [96] Eagan JM, Xu J, Di Girolamo R, Thurber CM, Macosko CW, La Pointe AM, et al. Combining polyethylene and polypropylene: enhanced performance with PE/iPP multiblock polymers. Science 2017;80. https://doi.org/10.1126/science. aah5744.
- [97] Omazic A, Oreski G, Edler M, Eder GC, Hirschl C, Pinter G, et al. Increased reliability of modified polyolefin backsheet over commonly used polyester backsheets for crystalline PV modules. J Appl Polym Sci 2020. https://doi.org/ 10.1002/app.48899.
- [98] Gong H, Wang G, Zheng L, Gao M. Reliability and durability impact of high UV transmission EVA for PV modules for the EU PVSEC 2015. 31st PVSEC; 2015.
- [99] Eder GC, Voronko Y, Oreski G, Mühleisen W, Knausz M, Omazic A, et al. Error analysis of aged modules with cracked polyamide backsheets. Sol Energy Mater Sol Cells 2019;203:110194. https://doi.org/10.1016/j.solmat.2019.110194.
- [100] Lyu Y, Kim JH, Fairbrother A, Gu X. Degradation and cracking behavior of polyamide-based backsheet subjected to sequential fragmentation test. IEEE J Photovoltaics 2018;8:1748–53. https://doi.org/10.1109/ JPHOTOV.2018.2863789.

- [101] Lyu Y, Fairbrother A, Gong M, Kim JH, Hauser A, O'Brien G, et al. Drivers for the cracking of multilayer polyamide-based backsheets in field photovoltaic modules: in-depth degradation mapping analysis. Prog Photovoltaics Res Appl 2020. https://doi.org/10.1002/pip.3260.
- [102] Tracy J, Choudhury KR, Gambogi W, Felder T, Garreau-Iles L, Hu H, et al. Survey of material degradation in globally fielded PV modules. In: IEEE 46th photovolt. Spec. Conf., IEEE; 2019. p. 874–9. https://doi.org/10.1109/ PVSC40753.2019.8981140.
- [103] Hirschl C, Biebl-Rydlo M, Debiasio M, Mühleisen W, Neumaier L, Scherf W, et al. Determining the degree of crosslinking of ethylene vinyl acetate photovoltaic module encapsulants - a comparative study. Sol Energy Mater Sol Cells 2013;116: 203–18. https://doi.org/10.1016/j.solmat.2013.04.022.
- [104] Omazic A, Oreski G, Halwachs M, Eder GC, Hirschl C, Neumaier L, et al. Relation between degradation of polymeric components in crystalline silicon PV module and climatic conditions: a literature review. Sol Energy Mater Sol Cells 2019;192: 123–33. https://doi.org/10.1016/j.solmat.2018.12.027.
- [105] Miller DC, Morse J, Tappan IA, Eafanti JJ, McDanold BK, Lockman T, et al. Comparison of breakdown-voltage of contemporary and veteran photovoltaic backsheets. Sol Energy 2019;182:29–41. https://doi.org/10.1016/j. solener.2019.01.092.
- [106] Reil F, Althaus J, Vaaßen W, Herrmann W. The effect of transportation impacts and dynamic load tests on the mechanical and electrical Behaviour of Crystalline PV Modules. Proc. 25th EU PVSEC; 2010.
- [107] Olschok C, Pfeiffer M, Zech M, Schmid M, Zehner M, Gerd B. Untersuchung von Handhabungsfehlern bei der Montage und Installation von PV-Modulen Motivation und Zielsetzung. Top 50 Sol Expert 2012.
- [108] Jordan DC, Silverman TJ, Wohlgemuth JH, Kurtz SR, VanSant KT. Photovoltaic failure and degradation modes. Prog Photovoltaics Res Appl 2017;25:318–26. https://doi.org/10.1002/pip.2866.
- [109] Quintana MA, King DL, McMahon TJ, Osterwald CR. Commonly observed degradation in field-aged photovoltaic modules. In: IEEE 29th photovolt. Spec. Conf. Institute of Electrical and Electronics Engineers Inc.; 2002. p. 1436–9. https://doi.org/10.1109/PVSC.2002.1190879.
- [110] Halwachs M, Neumaier L, Vollert N, Maul L, Dimitriadis S, Voronko Y, et al. Statistical evaluation of PV system performance and failure data among different climate zones. Renew Energy 2019;139:1040–60. https://doi.org/10.1016/j. renene.2019.02.135.
- [111] Smestad GP, Germer TA, Alrashidi H, Fernández EF, Dey S, Brahma H, et al. Modelling photovoltaic soiling losses through optical characterization. Sci Rep 2020;10:1–13. https://doi.org/10.1038/s41598-019-56868-z.
- [112] Costa SCS, Diniz ASAC, Kazmerski LL. Dust and soiling issues and impacts relating to solar energy systems: literature review update for 2012-2015. Renew Sustain Energy Rev 2016;63:33–61. https://doi.org/10.1016/j.rser.2016.04.059.
- [113] Kempe M. Overview of scientific issues involved in selection of polymers for PV applications. In: 2011 37th IEEE photovolt. Spec. Conf. IEEE; 2011. p. 85–90. https://doi.org/10.1109/PVSC.2011.6185851.
- [114] Virtuani A, Annigoni E, Ballif C. One-type-fits-all-systems: strategies for preventing potential-induced degradation in crystalline silicon solar photovoltaic modules. Prog Photovoltaics Res Appl 2019;27:13–21. https://doi.org/10.1002/ pip.3066.
- [115] Luo W, Khoo YS, Hacke P, Naumann V, Lausch D, Harvey SP, et al. Potentialinduced degradation in photovoltaic modules: a critical review. Energy Environ Sci 2017;10:43–68. https://doi.org/10.1039/c6ee02271e.
- [116] Miller DC, Bokria JG, Burns DM, Fowler S, Gu X, Hacke PL, et al. Degradation in photovoltaic encapsulant transmittance: results of the first PVQAT TG5 artificial weathering study. Prog Photovoltaics Res Appl 2019;27:391–409. https://doi. org/10.1002/pip.3103.
- [117] Lyu Y, Kim JH, Gu X. Developing methodology for service life prediction of PV materials: quantitative effects of light intensity and wavelength on discoloration of a glass/EVA/PPE laminate. Sol Energy 2018;174:515–26. https://doi.org/ 10.1016/j.solener.2018.08.067.
- [118] Peike C, Purschke L, Weiss KA, Kohl M, Kempe M. Towards the origin of photochemical EVA discoloration. In: Conf. Rec. IEEE photovolt. Spec. Conf. Institute of Electrical and Electronics Engineers Inc.; 2013. p. 1579–84. https:// doi.org/10.1109/PVSC.2013.6744447.
- [119] Sinha A, Sastry OS, Gupta R. Nondestructive characterization of encapsulant discoloration effects in crystalline-silicon PV modules. Sol Energy Mater Sol Cells 2016;155:234–42. https://doi.org/10.1016/j.solmat.2016.06.019.
- [120] Lyu Y, Fairbrother A, Kim JH, Gong M, Sung L, Watson SS, et al. Fluorescence imaging analysis of depth-dependent degradation in photovoltaic laminates: insights to the failure. Prog Photovoltaics Res Appl 2020;28:122–34. https://doi. org/10.1002/pip.3212.
- [121] Tracy J, Bosco N, Dauskardt R. Encapsulant adhesion to surface metallization on photovoltaic cells. IEEE J Photovoltaics 2017;7:1635–9. https://doi.org/ 10.1109/JPHOTOV.2017.2746572.
- [122] Kempe MD. Ultraviolet light test and evaluation methods for encapsulants of photovoltaic modules. Sol Energy Mater Sol Cells 2010;94:246–53. https://doi. org/10.1016/j.solmat.2009.09.009.
- [123] Jentsch A, Eichhorn KJ, Voit B. Influence of typical stabilizers on the aging behavior of EVA foils for photovoltaic applications during artificial UVweathering. Polym Test 2015;44:242–7. https://doi.org/10.1016/j. polymertesting.2015.03.022.
- [124] Gagliardi M, Paggi M. Long-term EVA degradation simulation: climatic zones comparison and possible revision of accelerated tests. Sol Energy 2018;159: 882–97. https://doi.org/10.1016/j.solener.2017.10.081.

- [125] Weber U, Eiden R, Strubel C, Soegding T, Heiss M, Zachmann P, et al. Acetic acid production, migration and corrosion effects in ethylene-vinyl- acetate- (EVA-) based pv modules. 27th Eur Photovolt Sol Energy Conf Exhib 2012:2992–5. https://doi.org/10.4229/27thEUPVSEC2012-4CO.9.4.
- [126] Xiong H, Gan C, Yang X, Hu Z, Niu H, Li J, et al. Corrosion behavior of crystalline silicon solar cells. Microelectron Reliab 2017;70:49–58. https://doi.org/10.1016/ j.microrel.2017.01.006.
- [127] Semba T, Shimada T, Shirasawa KYK, Takato H. Corrosion of the glass and formation of lead compounds in the metallization by high temperature and high humidity test of crystalline silicon PV module. In: 2018 IEEE 7th world conf. Photovolt. Energy conversion, WCPEC 2018 - a Jt. Conf. 45th IEEE PVSC, 28th PVSEC 34th EU PVSEC. Institute of Electrical and Electronics Engineers Inc.; 2018. p. 1333–5. https://doi.org/10.1109/PVSC.2018.8548005.
- [128] Tanahashi T, Sakamoto N, Shibata H, Masuda A. Localization and characterization of a degraded site in crystalline silicon photovoltaic cells exposed to acetic acid vapor. IEEE J Photovoltaics 2018;8:997–1004. https://doi.org/ 10.1109/JPHOTOV.2018.2839259.
- [129] López-Escalante MC, Caballero LJ, Martín F, Gabás M, Cuevas A, Ramos-Barrado JR. Polyolefin as PID-resistant encapsulant material in PV modules. Sol Energy Mater Sol Cells 2016;144:691–9. https://doi.org/10.1016/j. solmat.2015.10.009.
- [130] Zhang J wei, Cao D kun, Diaham S, Zhang X, qian Yin X, Wang Q. Research on potential induced degradation (PID) of polymeric backsheet in PV modules after salt-mist exposure. Sol Energy 2019;188:475–82. https://doi.org/10.1016/j. solener.2019.06.019.
- [131] Brecl K, Barretta C, Oreski G, Malic B, Topic M. The influence of the EVA film aging on the degradation behavior of PV modules under high voltage bias in wet conditions followed by electroluminescence. IEEE J Photovoltaics 2019;9: 259–65. https://doi.org/10.1109/JPHOTOV.2018.2875196.
- [132] Berghold J, Koch S, Frohmann B, Hacke P, Grunow P. Properties of encapsulation materials and their relevance for recent field failures. In: 2014 IEEE 40th photovolt. Spec. Conf. PVSC 2014. Institute of Electrical and Electronics Engineers Inc.; 2014. p. 1987–92. https://doi.org/10.1109/PVSC.2014.6925315.
- [133] Norris A, Ketola B. The role of encapsulant moisture permeability in the durability of solar photovoltaic modules. 25th Eur Photovolt Sol Energy Conf Exhib/5th World Conf Photovolt Energy Conversion 6-10 Sept 2010. https://doi.org/ 10.4229/25THEUPVSEC2010-4AV.3.43. Val Spain 2010:4098–102.
- [134] Dechthummarong C, Wiengmoon B, Chenvidhya D, Jivacate C, Kirtikara K. Physical deterioration of encapsulation and electrical insulation properties of PV modules after long-term operation in Thailand. In: Sol. Energy mater. Sol. Cells. vol. 94. North-Holland; 2010. p. 1437–40. https://doi.org/10.1016/j. solmat.2010.03.038.
- [135] Pérez B, Merino R, Fidalgo I. Lamination cycle time optimization using new POE encapsulants. 32nd Eur Photovolt Sol Energy Conf Exhib 2016;183–6. https://doi. org/10.4229/EUPVSEC20162016-1BV.5.41.
- [136] Harney R, Rabanal-Arabach J, Halm A, Merino Martínez R, Fidalgo JI, Schneider A. Material developments allowing for new applications, increased long term stability and minimized cell to module power losses. 31st Eur Photovolt Sol Energy Conf Exhib 2015;153–6. https://doi.org/10.4229/ EUPVSEC20152015-18V.6.36.
- [137] Boyce KP, Merzlic S, Fairbrother A, Gu X, Julien S, Wan K-T, et al. Degradation analysis of field-exposed photovoltaic modules with non-fluoropolymer-based backsheets. In: Kempe MD, Dhere NG, Sakurai K, editors. Reliab. Photovolt. Cells, modul. Components, syst. X, vol. 10370. SPIE; 2017. p. 2. https://doi.org/ 10.1117/12.2272488.
- [138] Wallner GM, Geretschläger KJ, Hintersteiner I, Buchberger W. Characterization of polyoxymethylene for backsheets of photovoltaic modules. J Plastic Film Sheeting 2017;33:345–60. https://doi.org/10.1177/8756087916666624.
- [139] Geretschläger KJ, Wallner GM, Hintersteiner I, Buchberger W, Geretschlager KJ, Wallner GM, et al. Damp heat aging behavior of a polyamide-based backsheet for photovoltaic modules. J Sol Energy Eng 2016;138:41003. https://doi.org/ 10.1115/1.4032977.
- [140] Geretschläger KJ, Wallner GM, Fischer J. Structure and basic properties of photovoltaic module backsheet films. Sol Energy Mater Sol Cells 2016;144:451–6. https://doi.org/10.1016/j.solmat.2015.09.060.
 [141] Kim N, Kang H, Hwang KJ, Han C, Hong WS, Kim D, et al. Study on the
- [141] Kim N, Kang H, Hwang KJ, Han C, Hong WS, Kim D, et al. Study on the degradation of different types of backsheets used in PV module under accelerated conditions. Sol Energy Mater Sol Cells 2014;120:543–8. https://doi.org/10.1016/ j.solmat.2013.09.036.
- [142] Klinke AG, Gok A, French RH, Bruckman LS, Ifeanyi SI. Degradation of photovoltaic backsheet materials under multi-factor accelerated UV light exposures. In: Kempe MD, Dhere NG, Sakurai K, editors. Reliab. Photovolt. Cells, modul. Components. Syst. X, SPIE; 2017. p. 3. https://doi.org/10.1117/ 12.2274108.
- [143] Fairbrother A, Boyd M, Lyu Y, Avenet J, Illich P, Wang Y, et al. Differential degradation patterns of photovoltaic backsheets at the array level. Sol Energy 2018;163. https://doi.org/10.1016/j.solener.2018.01.072.
- [144] Lefebvre AA, O'Brien GS, Douglas BS, Knapp JD, Garcia D, Moeller G. Durability of photovoltaic backsheet outer weatherable layers. In: 2015 IEEE 42nd photovolt. Spec. Conf. PVSC 2015. Institute of Electrical and Electronics Engineers Inc.; 2015. https://doi.org/10.1109/PVSC.2015.7355704.
- [145] Zhang Y, Xu J, Mao J, Tao J, Shen H, Chen Y, et al. Long-term reliability of silicon wafer-based traditional backsheet modules and double glass modules. RSC Adv 2015;5:65768–74. https://doi.org/10.1039/c5ra11224a.
- [146] Gambogi WJ. Comparative performance of backsheets for photovoltaic modules.
 25th Eur Photovolt Sol Energy Conf Exhib/5th World Conf Photovolt Energy

Conversion 6-10 Sept 2010. https://doi.org/10.4229/25THEUPVSEC2010-4AV.3.39. Val Spain 2010:4079–83.

- [147] Liu F, Jiang L, Yang S. Ultra-violet degradation behavior of polymeric backsheets for photovoltaic modules. Sol Energy 2014;108:88–100. https://doi.org/ 10.1016/j.solener.2014.06.027.
- [148] Lin C-C, Krommenhoek PJ, Watson SS, Gu X. Chemical depth profiling of photovoltaic backsheets after accelerated laboratory weathering. In: Dhere NG, Wohlgemuth JH, Jones-Albertus R, editors. Reliab. Photovolt. Cells, modul. Components, syst. VII, vol. 9179. SPIE; 2014. https://doi.org/10.1117/ 12.2066400. 91790R-91790R.
- [149] Sample T, Garreau-Iles LGA, Trout TJ, Stika KM, Kathmann EEL, Hamzavy B, et al. Backsheet and module durability and performance and comparison of accelerated testing to long term fielded modules. 28th Eur Photovolt Sol Energy Conf Exhib 2013:2846–50. https://doi.org/10.4229/28THEUPVSEC2013-4CO.10.2.
- [150] Lyu Y, Fairbrother A, Gong M, Kim JH, Gu X, Kempe M, et al. Impact of environmental variables on the degradation of photovoltaic components and perspectives for the reliability assessment methodology. Sol Energy 2020;199: 425–36. https://doi.org/10.1016/j.solener.2020.02.020.
- [151] Yang S, Jiang L. Crystalline silicon PV module field failures. Durab. Reliab. Polym. Other Mater. Photovolt. Modul. 2019. https://doi.org/10.1016/B978-0-12-811545-9.00008-2.
- [152] Gebhardt P, Bauermann LP, Philipp D. Backsheet chalking theoretical background and relation to backsheet cracking and insulation failures. 35st Eur. Photovolt. Sol. Energy Conf. 2018 Brussels.
- [153] Gordon DA, Gok A, Meyer CW, Fagerholm CL, Sweet NW, DeNoyer L, et al. Characterizing the weathering induced haze formation and gloss loss of poly (ethylene-terephthalate) via MaPd:RTS spectroscopy. Reliab Photovolt Cells, Modul Components, Syst IX 2016;9938. https://doi.org/10.1117/12.2238295. 993801-993801.
- [154] Voronko Y, Eder GC, Knausz M, Oreski G, Koch T, Berger KA. Correlation of the loss in photovoltaic module performance with the ageing behaviour of the backsheets used: influence of backsheet on photovoltaic module performance. Prog Photovoltaics Res Appl 2015;23:1501–15. https://doi.org/10.1002/ pip.2580.
- [155] Lin C-C, Lyu Y, Jacobs DS, Kim JH, Wan K-T, Hunston DL, et al. A novel test method for quantifying cracking propensity of photovoltaic backsheets after ultraviolet exposure. Prog Photovoltaics Res Appl 2019;27:44–54. https://doi. org/10.1002/pip.3038.
- [156] Klinke AG, Gok A, Ifeanyi SI, Bruckman LS. A non-destructive method for crack quantification in photovoltaic backsheets under accelerated and real-world exposures. Polym Degrad Stabil 2018;153:244–54. https://doi.org/10.1016/j. polymdegradstab.2018.05.008.
- [157] Julien SE, Kempe MD, Eafanti JJ, Morse J, Wang Y, Fairbrother AW, et al. Characterizing photovoltaic backsheet adhesion degradation using the wedge and single cantilever beam tests, Part II: accelerated tests. Sol Energy Mater Sol Cells 2020:211. https://doi.org/10.1016/j.solmat.2020.110524.
- [158] Tracy J, Bosco N, Novoa F, Dauskardt R. Encapsulation and backsheet adhesion metrology for photovoltaic modules. Prog Photovoltaics Res Appl 2017;25:87–96. https://doi.org/10.1002/pip.2817.
- [159] Voronko Y, Eder GC, Chernev BS, Knausz M, Oreski G, Koch T, et al. Analytical evaluation of the ageing induced changes of the adhesive within photovoltaic backsheets. 28st Eur. Photovolt. Sol. Energy Conf., WIP 2013:3037–42. https:// doi.org/10.4229/28thEUPVSEC2013-4AV.4.10.
- [160] Wu D, Zhu J, Betts TR, Gottschalg R. Degradation of interfacial adhesion strength within photovoltaic mini-modules during damp-heat exposure. Prog Photovoltaics Res Appl 2014;22:796–809. https://doi.org/10.1002/pip.2460.
- [161] Oreski G, Wallner GM. Delamination behaviour of multi-layer films for PV encapsulation. In: Sol. Energy mater. Sol. Cells. vol. 89. North-Holland; 2005. p. 139–51. https://doi.org/10.1016/j.solmat.2005.02.009.
- [162] Yuen PY, Moffitt SL, Novoa FD, Schelhas LT, Dauskardt RH. Tearing and reliability of photovoltaic module backsheets. Prog Photovoltaics Res Appl 2019; 27. https://doi.org/10.1002/pip.3144. pip.3144-pip.3144.
- [163] Gagliardi M, Paggi M. Multiphysics analysis of backsheet blistering in photovoltaic modules. Sol Energy 2019;183:512–20. https://doi.org/10.1016/j. solener.2019.03.050.
- [164] Munoz MA, Alonso-García MC, Vela N, Chenlo F. Early degradation of silicon PV modules and guaranty conditions. Sol Energy 2011. https://doi.org/10.1016/j. solener.2011.06.011.
- [165] Chattopadhyay S, Dubey R, Kuthanazhi V, John JJ, Solanki CS, Kottantharayil A, et al. Visual degradation in field-aged crystalline silicon PV modules in India and correlation with electrical degradation. IEEE J Photovoltaics 2014;4:1470–6. https://doi.org/10.1109/JPHOTOV.2014.2356717.
- [166] Dhere NG. Flexible packaging for PV modules. In: Dhere NG, editor. Reliab. Photovolt. Cells, modul. Components, syst., vol. 7048. SPIE; 2008. 70480R. https://doi.org/10.1117/12.795718.
- [167] Martins AC, Chapuis V, Virtuani A, Ballif C. Robust glass-free lightweight photovoltaic modules with improved resistance to mechanical loads and impact. IEEE J Photovoltaics 2019;9:245–51. https://doi.org/10.1109/ JPHOTOV.2018.2876934.
- [168] Planes E, Yrieix B, Bas C, Flandin L. Chemical degradation of the encapsulation system in flexible PV panel as revealed by infrared and Raman microscopies. Sol Energy Mater Sol Cells 2014;122:15–23. https://doi.org/10.1016/j. solmat.2013.10.033.

- [169] Kempe M. Modeling of rates of moisture ingress into photovoltaic modules. Sol Energy Mater Sol Cells 2006;90:2720–38. https://doi.org/10.1016/j. solmat.2006.04.002.
- [170] Shimpi TM, Moffett C, Sampath WS, Barth KL. Materials selection investigation for thin film photovoltaic module encapsulation. Sol Energy 2019;187:226–32. https://doi.org/10.1016/j.solener.2019.04.095.
- [171] Strevel N, Trippel L, Kotarba C, Khan I. Improvements in CdTe module reliability and long-term degradation through advances in construction and device innovation. Photovoltaics Int 2013;1–8.
- [172] Barth KL, Hemenway D. Progress toward developing a novel module architecture for increased reliability and reduced costs. IEEE 40th Photovolt Spec Conf PVSC 2014:166–9. https://doi.org/10.1109/PVSC.2014.6925483. 2014 2014.
- [173] Kempe MD, Dameron AA, Moricone TJ, Reese MO. Evaluation and modeling of edge-seal materials for photovoltaic applications. Conf Rec IEEE Photovolt Spec Conf 2010:256–61. https://doi.org/10.1109/PVSC.2010.5614463.
- [174] Caballero LJ, Sánchez-Friera P, Lalaguna B, Alonso J, Vázquez MA. Series resistance modelling of industrial screen-printed monocrystalline silicon solar cells and modules including the effect of spot soldering. Conf Rec 2006 IEEE 4th World Conf Photovolt Energy Conversion 2006;2:1388–91. https://doi.org/ 10.1109/WCPEC.2006.279710. WCPEC-4.
- [175] Schmitt P, Eberlein D, Voos P, Tranitz M, Wirth H. Metallographic preparation of solar cell samples for quality assurance and material evaluation. Energy Proc 2011;8:402–8. https://doi.org/10.1016/j.egypro.2011.06.157.
- [176] Bosco N, Silverman TJ, Kurtz S. The influence of PV module materials and design on solder joint thermal fatigue durability. IEEE J Photovoltaics 2016;6:1407–12. https://doi.org/10.1109/JPHOTOV.2016.2598255.
- [177] Lee EJ, Kim DS, Lee SH. Ni/Cu metallization for low-cost high-efficiency PERC cells. Sol Energy Mater Sol Cells 2002;74:65–70. https://doi.org/10.1016/S0927-0248(02)00049-1.
- [178] ur Rehman A, Lee SH. Review of the potential of the Ni/Cu plating technique for crystalline silicon solar cells. Materials (Basel) 2014;7:1318–41. https://doi.org/ 10.3390/ma7021318.
- [179] Ong KH, Agileswari R, Maniscalco B, Arnou P, Kumar CC, Bowers JW, et al. Review on substrate and molybdenum back contact in CIGS thin film solar cell. Int J Photoenergy 2018;2018. https://doi.org/10.1155/2018/9106269.
- [180] Kamada R, Yagioka T, Adachi S, Handa A, Tai KF, Kato T, et al. New world record Cu(In,Ga)(Se,S) 2 thin film solar cell efficiency beyond 22. In: 2017 IEEE 44th photovolt spec conf PVSC, vol. 2017; 2017. p. 1–5. https://doi.org/10.1109/ PVSC.2017.8366261.
- [181] Romeo A, Terheggen M, Abou-Ras D, Bätzner DL, Haug F-J, Kälin M, et al. Development of thin-film Cu(In,Ga)Se2 and CdTe solar cells. Prog Photovoltaics Res Appl 2004;12:93–111. https://doi.org/10.1002/pip.527.
- [182] Jubault M, Ribeaucourt L, Chassaing E, Renou G, Lincot D, Donsanti F. Optimization of molybdenum thin films for electrodeposited CIGS solar cells. Sol Energy Mater Sol Cells 2011;95:26–31. https://doi.org/10.1016/j. solmat.2010.12.011.
- [183] Orgassa K, Schock HW, Werner JH. Alternative back contact materials for thin film Cu(In,Ga)Se2 solar cells. Thin Solid Films 2003;431–432:387–91. https:// doi.org/10.1016/S0040-6090(03)00257-8.
- [184] Geipel T, Moeller M, Walter J, Kraft A, Eitner U. Intermetallic compounds in solar cell interconnections: microstructure and growth kinetics. Sol Energy Mater Sol Cells 2017;159:370–88. https://doi.org/10.1016/j.solmat.2016.08.039.
- [185] Walter J, Tranitz M, Volk M, Ebert C, Eitner U. Multi-wire interconnection of busbar-free solar cells. Energy Proc 2014;55:380–8. https://doi.org/10.1016/j. egypro.2014.08.109.
- [186] Cuddalorepatta G, Dasgupta A, Sealing S, Moyer J, Tolliver T, Loman J. Durability of Pb-free solder between copper interconnect and silicon in photovoltaic cells. Prog Photovoltaics Res Appl 2010;18:168–82. https://doi.org/10.1002/pip.944.
- [187] Powalla M, Paetel S, Ahlswede E, Wuerz R, Wessendorf CD, Magorian Friedlmeier T. Thin-film solar cells exceeding 22% solar cell efficiency: an overview on CdTe-, Cu(In,Ga)Se 2 -, and perovskite-based materials. Appl Phys Rev 2018;5. https://doi.org/10.1063/1.5061809.
- [188] Reinhard P, Chirila A, Blosch P, Pianezzi F, Nishiwaki S, Buechelers S, et al. Review of progress toward 20% efficiency flexible CIGS solar cells and manufacturing issues of solar modules. In: 2012 IEEE 38th photovolt. Spec. Conf. PART. vol. 2. IEEE; 2012. p. 1–9. https://doi.org/10.1109/PVSC-Vol2.2012.66565789.
- [189] Jeong JS, Park N, Han C. Field failure mechanism study of solder interconnection for crystalline silicon photovoltaic module. Microelectron Reliab 2012;52: 2326–30. https://doi.org/10.1016/j.microrel.2012.06.027.
- [190] Park NC, Jeong JS, Kang BJ, Kim DH. The effect of encapsulant discoloration and delamination on the electrical characteristics of photovoltaic module. Microelectron Reliab 2013;53:1818–22. https://doi.org/10.1016/j. microrel.2013.07.062.
- [191] Muñoz J, Lorenzo E, Martínez-Moreno F, Marroyo L, García M. An investigation into hot-spots in two large grid-connected PV plants. Prog Photovoltaics Res Appl 2008;16:693–701. https://doi.org/10.1002/pip.844.
- [192] Mathiak G, Althaus J, Menzler S, Lichtschläger L, Herrmann W. PV Module Corrosion from ammonia and salt mist - experimental study with full-size modules. In: 27th Eur. Photovolt. Sol. Energy conf. Exhib. WIP; 2012. p. 3536–40. https://doi.org/10.4229/27thEUPVSEC2012-4BV.3.44.
- [193] Yang TL, Huang KY, Yang S, Hsieh HH, Kao CR. Growth kinetics of Ag3Sn in silicon solar cells with a sintered Ag metallization layer. Sol Energy Mater Sol Cells 2014;123:139–43. https://doi.org/10.1016/j.solmat.2014.01.018.

- [194] Schmitt P, Kaiser P, Savio C, Tranitz M, Eitner U. Intermetallic phase growth and reliability of Sn-Ag-soldered solar cell joints. Energy Proc 2012;27:664–9. https:// doi.org/10.1016/j.egypro.2012.07.126.
- [195] Bosco N, Silverman TJ, Kurtz S. Climate specific thermomechanical fatigue of flat plate photovoltaic module solder joints. Microelectron Reliab 2016;62:124–9. https://doi.org/10.1016/j.microrel.2016.03.024.
- [196] Kraft A, Labusch L, Ensslen T, Durr I, Bartsch J, Glatthaar M, et al. Investigation of acetic acid corrosion impact on printed solar cell contacts. IEEE J Photovoltaics 2015;5:736–43. https://doi.org/10.1109/JPHOTOV.2015.2395146.
- [197] Walter J, Rendler LC, Ebert C, Kraft A, Eitner U. Solder joint stability study of wire-based interconnection compared to ribbon interconnection. Energy Proc 2017;124:515–25. https://doi.org/10.1016/j.egypro.2017.09.288.
- [198] Köntges M, Kajari-Schröder S, Kunze I, Jahn U. Crack statistic of crystalline silicon photovoltaic modules. IEA PVPS Task 2 Perform Anal 2011. https://doi.org/ 10.4229/26thEUPVSEC2011-4EO.3.6.
- [199] Köntges M, Kajari-Schröder S, Kunze I. Crack statistic for wafer-based silicon solar cell modules in the field measured by UV fluorescence. IEEE J Photovoltaics 2013; 3:95–101. https://doi.org/10.1109/JPHOTOV.2012.2208941.
- [200] Budiman AS, Illya G, Handara V, Caldwell WA, Bonelli C, Kunz M, et al. Enabling thin silicon technologies for next generation c-Si solar PV renewable energy systems using synchrotron X-ray microdiffraction as stress and crack mechanism probe. Sol Energy Mater Sol Cells 2014;130:303–8. https://doi.org/10.1016/j. solmat.2014.07.029.
- [201] Sander M, Dietrich S, Pander M, Schweizer S, Ebert M, Bagdahn J. Investigations on crack development and crack growth in embedded solar cells. Event SPIE Sol Energy + Technol 2011;8112:811209. https://doi.org/10.1117/12.893662.
- [202] Pingel S, Zemen Y, Frank O, Geipel T, Berghold J. Mechanical stability of solar cells within solar panels. Proc 24th EUPVSEC 2009. https://doi.org/10.4229/ 24thEUPVSEC2009-4AV.3.49.
- [203] Gabor A, Williams TK, Ralli M, Montminy S, Alegria L, Bordonaro C, et al. Soldering induced damage to thin Si solar cells and detection of cracked cells in modules. In: 21st Eur. Photovolt. Sol. Energy conf. Germany: Dresden; 2006.
- [204] Teubner J, Buerhop C, Pickel T, Hauch J, Camus C, Brabec CJ. Quantitative assessment of the power loss of silicon PV modules by IR thermography and its dependence on data-filtering criteria. Prog Photovoltaics Res Appl 2019;27: 856–68.
- [205] Kontges M, Kunze I, Kajari-Schröder S, Breitenmoser X, Bjørneklett B. Quantifying the risk of power loss in PV modules due to micro cracks. 25th Eur Photovolt Sol Energy Conf Exhib 2010:6–10. https://doi.org/10.4229/25thEUPVSEC2010-4BO.9.4.
- [206] Jürgen Arp BJ. Long term statistics ON micro cracks and their impact ON performance. In: 31st Eur. Photovolt. Sol. Energy conf. Exhib.; 2015. p. 2553–6.
- [207] Buerhop C, Schlegel D, Niess M, Vodermayer C, Weißmann R, Brabec CJ. Reliability of IR-imaging of PV-plants under operating conditions. Sol Energy Mater Sol Cells 2012;107:154–64. https://doi.org/10.1016/j. solmat.2012.07.011.
- [208] Kajari-Schröder S, Kunze I, Eitner U. Spatial and orientational distribution of cracks in crystalline photovoltaic modules generated by mechanical load tests. Sol Energy Mater Sol Cells 2011.
- [209] Simon M, Meyer EL. Detection and analysis of hot-spot formation in solar cells. Sol Energy Mater Sol Cells 2010;94:106–13. https://doi.org/10.1016/j. solmat.2009.09.016.
- [210] Herrmann W, Wiesner W, Vaassen W. Hot spot investigations on PV modules new concepts for a test standard and consequences for module design with respect to bypass diodes. Conf Rec IEEE Photovolt Spec Conf 1997:1129–32. https://doi. org/10.1109/pvsc.1997.654287.
- [211] Gostein M, Dunn L. Light soaking effects on photovoltaic modules: overview and literature review. Conf Rec IEEE Photovolt Spec Conf 2011:3126–31. https://doi. org/10.1109/PVSC.2011.6186605.
- [212] Bothe K, Schmidt J. Electronically activated boron-oxygen-related recombination centers in crystalline silicon. J Appl Phys 2006;99:13701. https://doi.org/ 10.1063/1.2140584.
- [213] Nagel H, Metz A, Wangemann K. Crystalline si solar cells and modules featuring excellent stability against potential-induced degradation. 26th Eur Photovolt Sol Energy Conf Exhib 2011:3107–12. https://doi.org/10.4229/26thEUPVSEC2011-4CO.5.6.
- [214] Ikkurti HP, Saha S. A comprehensive techno-economic review of microinverters for Building Integrated Photovoltaics (BIPV). Renew Sustain Energy Rev 2015;47: 997–1006. https://doi.org/10.1016/j.rser.2015.03.081.
- [215] Gu Y, Li W, Zhao Y, Yang B, Li C, He X. Transformerless inverter with virtual DC bus concept for cost-effective grid-connected PV power systems. IEEE Trans Power Electron 2013;28:793–805. https://doi.org/10.1109/TPEL.2012.2203612.
- [216] Aghaei M. Novel methods in control and monitoring of photovoltaic systems. Ph. D Thesis. Politecnico di Milano: 2016.
- [217] Quater PB, Grimaccia F, Leva S, Mussetta M, Aghaei M. Light unmanned aerial vehicles (UAVs) for cooperative inspection of PV plants. IEEE J Photovoltaics 2014;4:1107–13. https://doi.org/10.1109/JPHOTOV.2014.2323714.
- [218] Kirsten Vidal de Oliveira A, Aghaei M, Rüther R. Aerial infrared thermography for low-cost and fast fault detection in utility-scale PV power plants. Sol Energy 2020. https://doi.org/10.1016/j.solener.2020.09.066.
- [219] Grimaccia F, Leva S, Dolara A, Aghaei M. Survey on PV modules' common faults after an O&M flight extensive campaign over different plants in Italy. IEEE J Photovoltaics 2017;7:810–6.
- [220] Moradi AM, Aghaei M, Esmailifar SM. A deep convolutional encoder-decoder architecture for autonomous fault detection of PV plants using multi-copters solar energy. Sol Energy 2021. https://doi.org/10.1016/j.solener.2021.05.029.

Renewable and Sustainable Energy Reviews 159 (2022) 112160

- [221] Dhere NG, Shiradkar N, Schneller E, Gade V. The reliability of bypass diodes in PV modules. Reliab Photovolt Cells, Modul Components, Syst VI 2013;8825:88250I. https://doi.org/10.1117/12.2026782.
- [222] Shin WG, Lim JR, Kang GH, Ju YC, Hwang HM, Ko SW. Current flow analysis of pv arrays under voltage mismatch conditions and an inverter failure. Appl Sci 2019;9. https://doi.org/10.3390/app9235163.
- [223] Shiradkar N, Gade V, Sundaram K. Predicting service life of bypass diodes in photovoltaic modules. IEEE 42nd Photovolt Spec Conf PVSC 2015 2015. https:// doi.org/10.1109/PVSC.2015.7355606. 2015.
- [224] Zhang Z, Wohlgemuth J, Kurtz S. The thermal reliability study of bypass diodes in photovoltaic modules. In: Pvmw. vol. 13. NREL; 2013. p. 58225.
- [225] Eskandari A, Milimonfared J, Aghaei M. Fault detection and classification for photovoltaic systems based on hierarchical classification and machine learning technique. IEEE Trans Ind Electron 2020. https://doi.org/10.1109/ TIE.2020.3047066.
- [226] Eskandari A, Milimonfared J, Aghaei M. Line-line fault detection and classification for photovoltaic systems using ensemble learning model based on I-V characteristics. Sol Energy 2020;211:354–65. https://doi.org/10.1016/j. solener.2020.09.071.
- [227] Kalejs J. Junction box wiring and connector durability issues in photovoltaic modules. Reliab Photovolt Cells, Modul Components, Syst VII 2014;9179:91790S. https://doi.org/10.1117/12.2063488.
- [228] Chang M, Chen C, Hsueh CH, Hsieh WJ, Yen E, Ho KL, et al. The reliability investigation of PV junction box based on 1GW worldwide field database. In: 2015 IEEE 42nd photovolt Spec conf PVSC. vol. 2015; 2015. p. 6–9. https://doi. org/10.1109/PVSC.2015.7356130.
- [229] Leva S, Aghaei M. Failures and defects in PV systems review and methods of analysis. In: Badescu Viorel, George Cristian Lazaroiu LB, editors. Power Eng. Adv. Challenges Part B Electr. Power. first ed. CRC Press; 2018. p. 56–84.
- [230] Burgess C, Detweiler S, Needham C, Oudheusden F. Solar under storm Part II select best practices for resilient roof-mount PV systems with hurricane exposure. 2020. https://now.solar/2020/06/01/solar-under-storm-part-ii-rooftop-best-p ratices/.

- [231] Köntges M, Oreski G, Jahn U, Herz M, Hacke P, Weiß K-A. Assessment of photovoltaic module failures in the field: international energy agency photovoltaic power systems programme: IEA PVPS task 13. Subtask 3: Report IEA-PVPS T13-09: 2017. International Energy Agency; 2017.
- [232] Jensen MA, Morishige AE, Hofstetter J, Needleman DB, Buonassisi T. Evolution of LeTID defects in p-type multicrystalline silicon during degradation and regeneration. IEEE J Photovoltaics 2017;7:980–7.
- [233] Lyu Y, Fairbrother A, Gong M, Kim JH, Hauser A, O'Brien G, et al. Drivers for the cracking of multilayer polyamide-based backsheets in field photovoltaic modules: in-depth degradation mapping analysis. Prog Photovoltaics Res Appl 2020;28: 704–16. https://doi.org/10.1002/pip.3260.
- [234] Kempe MD, Lockman T, Morse J. Development of testing methods to predict cracking in photovoltaic backsheets. In: 2019 IEEE 46th photovolt. Spec. Conf. IEEE; 2019. p. 2411–6.
- [235] Gambogi W, Felder T, MacMaster S, Roy-Choudhury K, Yu B-L, Stika K, et al. Sequential stress testing to predict photovoltaic module durability. In: 2018 IEEE 7th world conf. Photovolt. Energy convers. (WCPEC)(A Jt. Conf. 45th IEEE PVSC, 28th PVSEC 34th EU PVSEC). IEEE; 2018. p. 1593–6.
- [236] Hacke P, Owen-Bellini M, Kempe M, Miller DC, Tanahashi T, Sakurai K, et al. Combined and sequential accelerated stress testing for derisking photovoltaic modules. In: Adv. Micro-and nanomater. Photovoltaics. Elsevier; 2019. p. 279–313.
- [237] Owen-Bellini M, Moffitt SL, Sinha A, Maes AM, Meert JJ, Karin T, et al. Towards validation of combined-accelerated stress testing through failure analysis of polyamide-based photovoltaic backsheets. Sci Rep 2021;11:1–13.
- [238] Oreski G, Stein J, Eder G, Berger K, Bruckman LS, Vedde J, et al. Designing new materials for photovoltaics: opportunities for lowering cost and increasing performance through advanced material innovations. Albuquerque, NM (United States): Sandia National Lab.(SNL-NM); 2021.
- [239] Peters IM, Hauch J, Brabec C, Sinha P. The value of stability in photovoltaics. Joule 2021.